

## Pt nanoclusters on GaN nanowires for solar-assisted seawater hydrogen evolution

Victor S. Batista<sup>2</sup>, Wan Jae Dong<sup>1</sup>, Yixin Xiao<sup>1</sup>, Ke R. Yang<sup>2</sup>, Zhengwei Ye<sup>1</sup>, Peng Zhou<sup>1</sup>, Ishtiaque Ahmed Navid<sup>1</sup>, & Zetian Mi<sup>1</sup>

<sup>1</sup>Department of Electrical Engineering and Computer Science, University of Michigan, 1301 Beal Avenue, Ann Arbor, MI 48109, USA. <sup>2</sup>Department of Chemistry and Energy Sciences Institute, Yale University, New Haven, CT 06520, USA.

E-mail: [victor.batista@yale.edu](mailto:victor.batista@yale.edu)

Seawater electrolysis provides a viable method to produce clean hydrogen fuel. To date, however, the realization of high-performance photocathodes for seawater hydrogen evolution reaction has remained challenging. Here, we introduce  $n^+p$  Si photocathodes with dramatically improved activity and stability for hydrogen evolution reaction in seawater, modified by Pt nanoclusters anchored on GaN nanowires (Fig 1). We find that Pt-Ga sites at the Pt/ GaN interface promote the dissociation of water molecules and spilling  $H^*$  over to neighboring Pt atoms for efficient  $H_2$  production. Pt/GaN/Si photocathodes achieve a current density of  $-10 \text{ mA/cm}^2$  at 0.15 and 0.39 V vs. RHE and high applied bias photon-to-current efficiency of 1.7% and 7.9% in seawater (pH = 8.2) and phosphate-buffered seawater (pH = 7.4), respectively. We further demonstrate a record-high photocurrent density of  $\sim 169 \text{ mA/cm}^2$  under concentrated solar light (9 suns). Moreover, Pt/GaN/Si can continuously produce  $H_2$  even under dark conditions by simply switching the electrical contact. This work provides valuable guidelines to design an efficient, stable, and energy- saving electrode for  $H_2$  generation by seawater splitting.

