#### **2D Materials**

#### Room 122 - Session 2D+EM+MI+QS-WeM

### 2D Materials: Heterostructures, Twistronics, and Proximity Effects

Moderators: Aaron Bostwick, Advanced Light Source, Lawrence Berkeley National Laboratory, Tiancong Zhu, Purdue University

#### 8:00am 2D+EM+MI+QS-WeM-1 Van der Waals Semiconductors: From Stacking-Controlled Crystals to Unconventional Heterostructures, Peter Sutter, E. Sutter, University of Nebraska - Lincoln INVITED 2D materials have attracted broad interest due to novel properties that arise in atomically thin crystals. As interesting scientifically and important technologically, but much less explored are van der Waals (vdW) crystals that, assembled from 2D building blocks, lie between a monolayer and the bulk. In this regime, phenomena such as phase separation, transformations between crystal polymorphs, and competition between different stacking

registries provide unprecedented opportunities for controlling morphology, interface formation, and novel degrees of freedom such as interlayer twist. But going beyond a single layer also poses significant challenges, both due to the diversity of the possible few-layer structures and the difficulty of probing functionality such as optoelectronics and ferroics at the relevant length scales.

Here, we discuss our recent research that addresses these challenges focusing on group IVA chalcogenides, an emerging class of anisotropic layered semiconductors promising for energy conversion, optoelectronics, and information processing. Advanced *in-situ* microscopy provides insights into the growth process, interlayer twisting, and emerging functionality such as stacking-controlled ferroelectricity. Nanometer-scale electron excited spectroscopy identifies photonic light-matter hybrid states and reveals anisotropic and valley-selective charge carrier flows across interfaces in heterostructures. Our results highlight the rich sets of materials architectures and functionalities that can be realized in van der Waals crystals and heterostructures beyond the 2D limit.

#### 8:30am 2D+EM+MI+QS-WeM-3 Deterministic Assembly, Transfer, and Flipping of 2D Materials Using Tunable Polymer Films, *Jeffrey J. Schwartz, S. Le*, University of Maryland, College Park; *K. Grutter, A. Hanbicki, A. Friedman*, Laboratory for Physical Sciences

Assembly of two-dimensional (2D) materials into van der Waals heterostructures is a crucial step in creating precisely engineered nanoscale and quantum devices for use in a wide variety of spintronic, electronic, and other applications. Numerous strategies exist to pick-up, stack, transfer, and even flip over these atomically thin structures. One popular strategy leverages the ability to tune the adhesion between a polymer stamp and 2D sheets to pick-up, stack, and release structures at different temperatures. Although relatively easy to implement, this technique is tedious to perform and has a low throughput. Here, we demonstrate a significant improvement to a deterministic, all-dry, polymer-assisted transfer technique using polyvinyl chloride (PVC) thin films to manipulate 2D materials and to fabricate devices. We construct stamps from pairs of commercially available PVC films that controllably pick-up and release 2D sheets within known, overlapping temperature ranges. These mechanically durable stamps can be produced quickly and without the time-consuming preparation and annealing steps required by most other commonly used polymers. Importantly, these stamps not only facilitate deterministic transfer of 2D materials, but they also enable polymer-to-polymer transfer (e.g., between separate stamps) and flipping of material stacks to create inverted heterostructures that are important for many applications, including scanning tunneling microscopy measurements. We characterize the thermal transition properties of the PVC films employed here as well as assay the cleanliness and performance of devices produced using this technique. These improvements enable rapid production of 2D devices with fewer interactions required by the operator, which is especially significant when working in controlled environments (e.g., glovebox) or in remote or autonomously controlled contexts.

8:45am 2D+EM+MI+QS-WeM-4 Cleaning of Low-Dimensionality Materials: Challenge and Solutions, Jean-Francois de Marneffe, P. Wyndaele, M. Timmermans, C. Cunha, IMEC, Belgium; B. Canto, Z. Wang, AMO GmbH, Aachen, Germany; R. Slaets, G. He, I. Asselberghs, C. J. Lockhart de la Rosa, G. Sankar Kar, C. Merckling, S. De Gendt, IMEC, Belgium

Over the last few years, significant efforts have been made in exploring lowdimensionality materials such as single layer Graphene (SLG), transition metal dichalcogenides (TMDCs) and carbon nanotubes (CNTs), for a wide range of applications covering beyond CMOS logic, EUV pellicles, photonics, and sensing (amongst others). Due to their intrinsic 2D or 1D nature, these materials are highly sensitive to processing damage leading to stoichiometric changes or crystalline defects. Among the many manufacturing steps required for building devices, the cleaning of these systems is an absolute requirement and a bottleneck. Typically, during processing, residual polymers or carbon of ambient origin, do contaminate the surface leading to nanometric deposits that change the intrinsic transport/optical properties of the materials, and cause parasitic dielectric drift or high contact resistance. Wet cleaning, using organic solvents, is a mainstream approach, which proves to be inefficient for irreversibly physically adsorbed polymer residues. In this paper, we explore dry cleaning approaches, based on plasma treatment and UV cure. Plasmabased cleaning proves to be very efficient but leads to material damage, which can be minimized by tuning the average ion energy, the processing temperature, the plasma chemistry or adding a post-cleaning restoration step. For TMDCs, damage consist essentially in the creation of chalcogen vacancies, which lead to metal oxidation upon ambient exposure. For Graphene and CNTs, damage consist in carbon vacancies, causing lattice distortions, oxidation and ultimately a dramatic change of the material's transport properties. Part of this presentation will explore the use of UV cure, which is a known method for cleaning polymers from semiconductor surfaces.

#### 9:00am 2D+EM+MI+QS-WeM-5 Spin-Valley Physics in Mixed-Dimensional Van Der Waals Heterostructures, Vikram Deshpande, University of Utah INVITED

Spin-valley physics has become ubiquitous in 2D materials-based van der Waals (vdW) heterostructures, particularly those hosting flat bands, wherein various ground states with spin-valley character including magnetic, insulating and superconducting states have been observed. On the other hand, mixed dimensional vdW heterostructures, such as those between 2D and 1D materials have been less explored for intricate spinvalley physics. The reduced phase space for scattering in 1D in particular might lead to qualitatively different phenomena. We are guided by our studies of ultraclean carbon nanotube quantum dots wherein we have observed subtle effects from the degeneracy lifting between the speeds of right- and left-moving electrons within a given Dirac cone or valley. Bound states can be purely fast-moving or purely slow-moving, giving rise to incommensurate energy level spacings and a vernier spectrum. Using quantum interferometry [1] and Coulomb blockade spectroscopy [2] of such ultraclean carbon nanotube quantum dots, we have found evidence for this vernier spectrum. The addition-energy spectrum of the quantum dots reveals an energy-level structure that oscillates between aligned and misaligned energy levels. Our data find that the fast- and slow-moving bound states hybridize at certain gate voltages. We extend existing theory to show that our experiment probes the degree of isospin polarization/hybridization of the various quantum states probed in our system. As a result, gate-voltage tuning can select states with varying degrees of hybridization, suggesting numerous applications based on accessing this isospin degree of freedom in conjunction with 2D materials in the form of mixed dimensional vdW heterostructures. We have fabricated prototypical mixed dimensional vdW heterostructures between carbon nanotubes and 2D materials and extended our measurements to these structures. I will discuss our recent and ongoing work studying spinvalley physics in such systems.

#### References:

Lotfizadeh, N.; Senger, M. J.; McCulley, D. R.; Minot, E. D.; Deshpande, V. V.Quantum Interferences in Ultraclean Carbon Nanotubes. Phys. Rev.Lett.2021,126(21),216802.https://doi.org/10.1103/PhysRevLett.126.216802.

Berg, J.; Lotfizadeh, N.; Nichols, D.; Senger, M. J.; De Gottardi, W.; Minot, E. D.; Deshpande, V. V. Vernier Spectrum and Isospin State Control in Carbon Nanotube Quantum Dots. arXiv November 20, 2023. http://arxiv.org/abs/2311.12332.

9:30am 2D+EM+MI+QS-WeM-7 Exploring Incommensurate Lattice Modulations in BSCCO van der Waals Heterostructures: Implications for Q-Bit Development, Patryk Wasik, Brookhaven National Laboratory; S. Zhao, Harvard University; R. Jangid, Brookhaven National Laboratory; A. Cui, Harvard University; J. Sinsheimer, Brookhaven National Laboratory; P. Kim, Harvard University; N. Poccia, IFW Dresden, Germany; C. Mazzoli, Brookhaven National Laboratory

Quantum computers (QC) are poised to revolutionise computational capabilities by naturally encoding complex quantum computations, thereby

significantly improving computation time compared to silicon-based technologies. Currently, Q-bits, the essential components of QCs, are made from conventional superconductors that operate efficiently only near absolute zero temperatures. To address this limitation, two-dimensional van der Waals (vdW) encapsulated high-temperature superconductor (HTSC) stacks have been proposed as future Q-bit candidates, driven by recent advancements in nanofabrication techniques. However, a detailed understanding of their structural and electronic properties is crucial.

We present low-temperature resonant soft X-ray investigations on ultrathin Bi<sub>2</sub>Sr<sub>2</sub>CaCu<sub>2</sub>O<sub>8+y</sub> (BSCCO) vdW heterostructures, promising candidates for large-scale Q-bit applications. BSCCO crystals exhibit two incommensurate lattice modulations (ILMs), providing an excellent opportunity to explore the relationship between structure and electronic behaviour in low dimensions. We report ILMs (Cu *L*<sub>3</sub>) and structural peak (off resonance) maps obtained across the superconducting transition temperature (T<sub>c</sub>  $\approx$  60 K). These signals, under external gating, present significant potential for further exploration offering new insights into the electronic interactions in vdW HTSC systems.

11:00am 2D+EM+MI+QS-WeM-13 Atomic Layer Deposition of Transition Metal Dichalcogenides: Precursors, Processes, and Applications Perspectives, Thong Ngo, A. Azcatl, N. Vu, C. Cheng, M. Miller, C. Chen, R. Kanjolia, M. Moinpour, M. Clark, EMD Electronics, USA INVITED Transition metal dichalcogenides (TMD) are three-atom-thick layer materials that possess a wide array of properties, such as insulating, semiconducting, conducting, and superconducting. While there has been a significant amount of research on TMD for various applications including energy storage, photovoltaics, biomedicals, catalysis, hydrogen production processes, and healthcare, the usage of TMD for electronic applications has been researched most in the past two decades.

Each layer of TMD is a 2D sheet with the thickness of ~6-7Å. These layers are bonded by Van der Waals force. The ultra-thin structure enables TMD for semiconductor industry applications, which continuously requires both size-scaling of materials layers and electrical performance improvement of devices. The semiconductor-range band gap and the high electron/hole mobility of several TMD, such as MoS<sub>2</sub>, WS<sub>2</sub>, WSe<sub>2</sub>, and MoSe<sub>2</sub>allow their usage for high mobility ultra-thin channel transistor. In addition, the relatively high conductivity of some other TMD, such as TaS<sub>2</sub> and NbS<sub>2</sub> make them promising candidates for interconnect barrier/liner as a replacement of TaN/Ta bilayer.

TMD materials need to pass certain quality requirements to provide desirable property/performance; therefore, method of synthesizing TMD plays an important role for high quality materials. Solution-based deposition, non-vacuum electrodeposition, polymer-assisted deposition, physical vapor deposition (PVD), chemical vapor deposition (CVD), and atomic layer deposition (ALD) have been used to deposit ultra-thin TMD. Among these techniques, CVD is the most popular deposition method, and to date, the highest quality of TMD for semiconductor applications is CVD-TMD. However, the need of lower thermal budget, better layer controllability, uniformity, and conformality requires the semiconductor community to explore ALD methods. In this presentation, we will review multiple ALD processes for TMD including precursors, process requirements for high mobility channel and barrier/liner applications. We will highlight challenges of TMD applications for logic, memory, and interconnects. The presentation will also feature our recent work on ALD MoS<sub>2</sub> for highmobility channel transistor with >5 decades On/Off ratio and >1  $\mu$ A/ $\mu$ m Ion. Our achievement of 300mm ALD MoS<sub>2</sub> deposition brings ultra-thin TMD materials closer to a manufacturable fab process for semiconductor industry.

#### 11:30am 2D+EM+MI+QS-WeM-15 Writing and Detecting Topological Spin Textures in Exfoliated Fe<sub>5</sub>-xGete<sub>2</sub>, *Luis Balicas*, Florida State University -National High Magnetic Field Lab - FSU Quantum Initiative

Fe<sub>5-x</sub>GeTe<sub>2</sub> is a centrosymmetric, layered van der Waals (vdW) ferromagnet that displays Curie temperatures  $T_c$  (270-330 K) that are within the useful range for spintronic applications. Little is known about the interplay between its topological spin textures (e.g., merons, skyrmions) with technologically relevant transport properties such as the topological Hall effect (THE), or topological thermal transport. We found via high-resolution Lorentz transmission electron microscopy that merons and anti-meron pairs coexist with Néel skyrmions in Fe<sub>5-x</sub>GeTe<sub>2</sub> over a wide range of temperatures and probe their effects on thermal and electrical transport [1]. It turns out that we detect a THE, even at room T, that senses merons at higher T's as well as their coexistence with skyrmions as T is lowered, indicating an on-demand thermally driven formation of either type of spin

texture.Remarkably, we also observe an unconventional THE, i.e., in absence of Lorentz force, and attribute it to the interaction between charge carriers and magnetic field-induced chiral spin textures. We find that both the anomalous Hall effect (AHE) and THE can be amplified considerably by just adjusting the thickness of exfoliated Fe5-xGeTe2, with the THE becoming observable even under zero magnetic field due to a field-induced unbalance in topological charges [2]. Using a complementary suite of techniques, including electronic transport, Lorentz transmission electron microscopy, and micromagnetic simulations, we reveal the emergence of substantial coercive fields upon exfoliation, which are absent in the bulk, implying thickness-dependent magnetic interactions that affect the topological spin textures (TSTs). We detected a 'magic' thickness of t ~30 nm where the formation of TSTs is maximized, inducing large magnitudes for the topological charge density, and the concomitant AHE and THE resistivities at T ~ 120 K. Their values are observed to be higher than those found in magnetic topological insulators and, so far, the largest reported for 2D magnets. The hitherto unobserved THE under zero magnetic field could provide a platform for the writing and electrical detection of TSTs aiming at energy-efficient devices based on vdW ferromagnets.

B. W. Casas *et al.*, Adv. Mater. **35**, 202212087 (2023).
A. Moon *et al.*, ACS Nano **18**, 4216-4228 (2024).

#### Magnetic Interfaces and Nanostructures Room 121 - Session MI+2D+AC+TF-WeM

#### **Altermagnetism and Spin-Dependent Systems**

Moderators: Markus Donath, Muenster University, Germany, Valeria Lauter, Oak Ridge National Laboratory

8:00am MI+2D+AC+TF-WeM-1 Twisted Electrons in Momentum Space: A Photoemission Perspective on Spin and Orbital Angular Momentum in Quantum Materials, Maximilian Ünzelmann, University of Würzburg, Germany; B. Geldiyev, Univsersity of Würzburg, Germany; T. Figgemeier, University of Würzburg, Germany; H. Bentmann, NTNU Trondheim, Norway; F. Reinert, Univsersity of Würzburg, Germany INVITED Beyond the spin, electronic states in crystalline solids can exhibit finite expectation values of orbital angular momentum (OAM). This phenomenon has attracted considerable attention in recent years and can particularly be traced back to the following key applications: (i) Since OAM is formed solely by inversion symmetry breaking (ISB) - and thus can also be present without magnetism or strong spin-orbit coupling (SOC) - it appears as an interesting quantum degree of freedom raising the potential of orbital analogs to spintronic phenomena, i.e. the field of orbitronics. (ii) OAM has been proposed to be a useful observable to assess nontrivial topology in the band structure of topological quantum matter. Lastly, if the atomic SOC strength is sizable, OAM is coupled to the electron spin giving rise to rich spin and orbital momentum space textures.

In this talk, I will shed light on those textures from the perspective of angleresolved photoemission spectroscopy (ARPES). Combining ARPES with lightpolarization-dependent and spin-resolved measurements allows us to address the momentum-dependent properties of the spatial and spin part of the wave functions, respectively. I will present experimental results on model-like monolayer systems and topological quantum materials and show that – as well as how – the complex interplay of ISB and SOC forms striking spin-orbital textures. Based on these findings, I will discuss the potential of utilizing OAM (i) towards orbitronic transport and (ii) to detect unexpected topological features.

8:30am MI+2D+AC+TF-WeM-3 Falicov Student Award Finalist Talk: Gap Tuning by Hole Doping in EuZn2As2 Semimetal, *Dejia Kong*<sup>1</sup>, University of Virginia; S. Karbasizadeh, University of South Carolina; G. Narasimha, Oak Ridge National Laboratory; P. Regmi, University of South Carolina; C. Tao, Oak Ridge National Laboratory; S. Mu, University of South Carolina; R. Vasudevan, Oak Ridge National Laboratory; I. Harrison, University of Virginia; R. Jin, University of South Carolina; Z. Gai, Oak Ridge National Laboratory

 $EuZn_2As_2$  is an ideal candidate for topological magnetism study in comparison to other europium-based semimetals that exhibit a similar type of magnetic transition from the antiferromagnetic phase to the

<sup>1</sup> Falicov Student Award Finalist

ferromagnetic phase at a low temperature. <sup>1</sup> Theoretical calculations predict gapped and flatter bands in EuZn<sub>2</sub>As<sub>2</sub> but a gapless  $\Gamma$  point in EuCd<sub>2</sub>As<sub>2</sub>.<sup>2</sup> In this work, a low-temperature cleaved EuZn<sub>2</sub>As<sub>2</sub> crystal is studied using scanning tunneling microscopy/spectroscopy (STM/S) and density functional theory (DFT). A group of triangular-shaped defects in combining with the DFT calculations are used to identify the existence of the europium-terminated and arsenic-terminated surfaces at the cleavage. Large bandgaps are observed on the two pristine terminations. However, the bandgap width is found to be very sensitive to local heterogenous, like defects and step edges. Two defect groups that create local electron deficiency, i.e. substitutional defect of As replacing Zn, and Zn vacancy, can drastically lower the bandgap. Furthermore, the modification of the bandgap width shows a discrepancy on the two terminations, bigger on Eu termination but much smaller on As-Zn termination. So, we predict that purposely hole doping the system during the crystal growth stage may create a new topological semimetal material with a gapless europium layer sandwiched by a gapped As-Zn lattice.

Reference:

1 Blawat, J. et al. Unusual Electrical and Magnetic Properties in Layered EuZn2As2. Adv Quantum Technol **5** (2022).

2 Wang, Z. C. *et al*. Anisotropy of the magnetic and transport properties of EuZn2As2. *Phys Rev B* **105** (2022).

#### 8:45am MI+2D+AC+TF-WeM-4 Characterization of LaMnO<sub>3</sub>/SrTiO<sub>3</sub> Thin Films and Its Mn Valance State Correlated with Ferromagnetism, *Ghadendra Bhandari, P. Tavazohi, V. Dewasurendra, M. Johnson, M. Holcomb*, West Virginia University

Thin films of  $LaMnO_3$  (LMO) / SrTiO<sub>3</sub> (STO) perovskite have gained interest for their abilities to be an essential component of some heterostructures while still exhibiting an interesting magnetic phase diagram. We have grown LaMnO<sub>3</sub> thin films on SrTiO<sub>3</sub> using pulsed laser deposition and deposition has been monitored by reflection high energy electron diffraction (RHEED) to verify layer-by-layer growth. Structure and magnetic properties have been characterized by X-ray diffractometry (XRD), and vibration sample magnetometry (VSM). LaMnO3 thin films exhibit ferromagnetic FM phases whereas bulk LaMnO3 is antiferromagnetic A-type. All thin films are coherently strained, forcing them to have the in-plane lattice parameter of the STO substrate (3.905 Å), but the out-of-plane parameter varies (3.89-3.93 Å). The variation in the c-lattice is developed from  $O_2$  growth pressure and consequently the Mn cation is in mixed valence state Mn<sup>3+/4+</sup>. The valence state of the Mn cation is realized from XPS and XAS study. The ferromagnetic magnetization is originated by the double exchange of Mn<sup>3+</sup>-O-Mn<sup>4+</sup>. The thickness averaged magnetizations from PNR measurements are comparable with magnetization obtained from VSM. The strength of magnetization correlates with content of Mn4+.

#### 9:00am MI+2D+AC+TF-WeM-5 Altermagnetism: From Spintronics to Unconventional Magnetic Phases, Libor Šmejkal, Uni Mainz, Germany INVITED

The search for unconventional quantum phases that break the symmetries of the crystal lattice has been a focus in physics since the early days of quantum theory, driven by both fundamental interest and potential applications. Prominent examples include cuprate superconductors, which are known for their unconventional d-wave Cooper pairing, and dissipationless transport.

In this presentation, we will discuss our recent discovery[1] of an unconventional magnetic phase motivated by our earlier predictions and observations of unconventional spintronics effects [2,3,4]. This unconventional phase, altermagnetism (see Figure), unlike common ferromagnetism and antiferromagnetism, breaks the symmetries of the crystal lattice, and features d, g, or i-partial wave characteristics simultaneously in its spin and electronic structure[1]. D-wave altermagnetism thus represents magnetic analogue of d-wave superconductivity.

We identified altermagnetism by employing and developing a symmetry framework that considers paired transformations involving electron spin and the crystal lattice. This framework is emerging as a new paradigm in the study of magnetic crystals. We will demonstrate its usefulness by discussing (i) the altermagnetic band structure of the semiconductor MnTe, which we recently experimentally observed through collaborative work using photoemission spectroscopy[5], and (ii) our identification of more than 240 realistic altermagnetic candidates.

Additionally, we will explore the rapid expansion of altermagnetic concepts to many fields with focus on ultrafast spintronics memories[6],

dissipationless transport [2-4] and two-dimensional band topology [7]. Finally, we will outline the latest developments in the field, including the theoretical identification of the magnetic analog of superfluid helium-3 and we will propose transport experiments which can be used for its detection[8].

[1] L. Šmejkal, J. Sinova, and T. Jungwirth, Phys. Rev. X 12, 031042 (2022)

[2] L. Šmejkal, et al., Sci. Adv. 6, eaaz8809 (2020)

[3] I. Mazin ,et al., PNAS 118, e2108924118 (2021)

[4] H. Reichlová, et al., Nature Communications 15, 4961 (2024)

[5] J. Krempasky\*, L. Šmejkal\*, S. Souza\*, et al., Nature, 626, 517 (2024)

[6] L. Šmejkal et al., Phys. Rev. X 12, 011028 (2022)

[7] I. Mazin, R. Gonzalez-Hernandez, and L. Šmejkal, arXiv:2309.02355 (2023)

[8] Birk Hellenes, et al., arXiv:2309.01607v2 (2024)

9:30am MI+2D+AC+TF-WeM-7 Growth Study of Kagome-structured Mn<sub>3</sub>Sn on Gallium Nitride (000\_1) Using Molecular Beam Epitaxy, H. Hall, S. Upadhyay, T. Erickson, A. Shrestha, A. Abbas, Arthur Smith, Ohio University Over the past few years, there has been a large amount of interest in Kagome-structured magnetic materials with non-collinear antiferromagnetic ordering [1]. Such materials show interesting magnetic properties including anomalous Hall effect and topological Hall effect [2]. In recent work, we have reported growth of Mn<sub>3</sub>Sn on sapphire (0001) which resulted in either a-plane or c-plane film orientations [3,4]. The substrate however was not ideal, and frequently we observed the disappearance of the diffraction pattern upon opening the Mn and Sn shutters with the pattern reappearing after some amount of resting time. In the case of the cplane orientation, theory suggested this could be due to interfacial disordering of the lattice. This might be due to the ~19% lattice mismatch which also is one reason for the preferred growth of a-plane oriented Mn<sub>3</sub>Sn on sapphire (0001) due to the much smaller lattice mismatch (<5%) along that direction. Nonetheless, high quality films prove difficult to obtain on sapphire (0001), and a better substrate is desirable. As such, we have investigated the growth of Mn<sub>3</sub>Sn films on freshly grown gallium nitride surfaces. The Mn<sub>3</sub>Sn growth follows immediately after the growth of Npolar GaN (0001), thus giving a perfectly clean and well-ordered substrate surface with only ~2.66% lattice mismatch along the 30° line to the high symmetry axis of GaN. We have investigated this as a function of substrate temperature and find an optimal temperature range in which streaky and clear RHEED patterns are obtained from the beginning of the growth. Next plans include studying of this surface with high-resolution STM and spinpolarized STM. This research has been supported by the U.S. Department of Energy, Office of Basic Energy Sciences, Division of Materials Sciences and Engineering under Award No. DE-FG02-06ER46317.

[1] H. Yang et al., New J. of Physics **19**, 015008 (2017).

[2] S. Nakatsuji, N. Kiyohara, and T. Higo, Nature 527, 212 (2015).

[3] S. Upadhyay et al., J. Vac. Sci. & Technol. A 41, 042710 (2023).

[4] S. Upadhyay et al., Surfaces and Interfaces 42, 103379 (2023).

#### 9:45am MI+2D+AC+TF-WeM-8 Exchange Bias Effect in Single-Layer Antiferromagnetic Mn3GaN Films, *Ali Abbas, A. Shrestha,* Ohio University; *D. Russell, F. Yang,* The Ohio State University; *A. Smith,* Ohio University

Strain-induced spin structures in non-collinear antiferromagnetic materials like Mn<sub>3</sub>GaN can be controlled by an external magnetic field[1][2]. In this work, we report the intrinsic exchange bias in the "single" antiferromagnetic Mn<sub>3</sub>GaN films fabricated by epitaxial growth of Mn<sub>3</sub>GaN on MgO (001) substrate using molecular beam epitaxy under in-plane tensile and out-of-plane compressive strain. Scanning transmission electron microscopy confirms significant strain at the Mn<sub>3</sub>GaN/MgO interface due to substrate induced tetragonal distortion. Superconducting quantum interference device measurements reveal an exchange bias field (Heb=1225 Oe) and a vertical magnetization shift below 300 K. Furthermore, magnetization M vs. the applied field H measurements from 300K down to 50K reveal the consistent horizontal and vertical shift of the hysteresis loop, which are usually observed only in ferro-/antiferromagnetic bilayers. Here, the exchange bias effect may be attributed to strain, leading to canted and uncompensated Mn spins coupled with an upper antiferromagnetic region, as reported in another system [2][3]. The findings of strain-induced exchange bias in antiferromagnetic Mn<sub>3</sub>GaN films may open a new route/ novel system for spintronic properties by design. This research has been supported by the U.S. Department of Energy, Office of Basic Energy Sciences, Division of

Materials Sciences and Engineering under Award No. DE–FG02–06ER46317 (work done at Ohio University, not including XRD) and under award No. DE– SC0001304 (XRD and SQUID measurements done at The Ohio State University).

#### References:

[1] X.F. Zhouet al., "Exchange Bias in Antiferromagnetic Mn3Sn Monolayer Films," Physical Review Applied, 14(5), 054037 (2020).

[2] B. Cuiet al., "Strain engineering induced interfacial self-assembly and intrinsic exchange bias in a manganite perovskite film". Scientific reports, 3(1), 2542, (2013).

[3] L. Wanget al., "Exchange bias and vertical shift of the magnetic hysteresis loop in Co/BiFeO3 bilayers. Ferroelectrics Letters Section, 48(4–6), 65–71, (2021).

11:00am MI+2D+AC+TF-WeM-13 L-Gap Surface Resonance at Pt(111): Influence of Atomic Structure, d Bands, and Spin-Orbit Interaction, Markus Donath, F. Schöttke, P. Krüger, University of Münster, Germany; L. Hammer, T. Kißlinger, M. Schneider, University of Erlangen-Nürnberg, Germany

Pt(111) hosts a surface resonance with peculiar properties concerning energy vs momentum dispersion and spin texture. At variance with the free-electronlike behavior of the L-gap Shockley-type surface states on the fcc(111) surfaces of Au, Ag, and Cu, it splits into several branches with distinct spin polarization around the center of the surface Brillouin zone. Theoretical predictions based on density-functional theory vary depending on the particular functionals used. To clarify this issue, we investigate the atomic structure of Pt(111) by low-energy electron diffraction and the unoccupied electronic structure by spin- and angle-resolved inverse photoemission. The experimental results are backed by theoretical studies using different functionals which show that the characteristics of the surface band depend critically on the lattice constant. We identified a delicate interplay of several contributions: Lattice constant, hybridization with d bands, and the influence of spin-orbit interaction are critical ingredients for understanding the peculiar energy dispersion and spin character of the unoccupied surface resonance.

11:15am MI+2D+AC+TF-WeM-14 Substrate-Induced Strain Effects on SrFeO<sub>3</sub> Thin Films, *Lucas Barreto*, University of Pennsylvania; *P. Rogge, J. Wang, B. Lefler,* Drexel University; *D. Puggioni, J. Rondinelli,* Northwestern University; *S. Koroluk, R. Green,* University of Saskatchewan, Canada; *S. May,* Drexel University

Materials with non-trivial magnetic ordering give rise to exotic topological phenomena that can enhance spin-based devices' performance. In this scenario, the cubic perovskite SrFeO<sub>3</sub> exhibits a rich magnetic ordering, described by a multi-**q** magnetic arrangement. In this work, we evaluate how in-plane lattice stress influences the structural, magnetic, and electronic of SrFeO<sub>3</sub> films. We grow epitaxial SrFeO<sub>3</sub> films on different substrates to induce compressive and tensile strains, characterize them using X-ray diffraction, and probe the electronic transport as a function of temperature. The experimental data are supported by density functional theory calculations, from which we obtain the structural and electronic properties of the strained SrFeO<sub>3</sub> structure. We map the magnetic ordering via resonant x-ray magnetic diffraction and observe shifts in the projection of the magnetic wavevector **q** along the [111] direction. Our results indicate that the lattice strain can tune the magnetic propagation vector on the films while maintaining the SrFeO<sub>3</sub> metallic behavior.

11:30am MI+2D+AC+TF-WeM-15 Tunable Localized Currents at Crystallographic Domain Boundaries in Altermagnet RuO2, Gina Pantano, E. Thareja, University of South Florida; L. Šmejkal, the Czech Academy of Sciences and Johannes Gutenberg Universität Mainz, Germany; J. Sinova, Johannes Gutenberg Universität Mainz, Germany; J. Gayles, University of South Florida

Research on interfacial phenomena in condensed matter physics has garnered significant interest over the last few decades due to the discovery of new properties and phases distinct from the bulk, enabling the manipulation of materials for technological applications. In this work, we investigate the novel effects that arise from the presence of a locally chiral crystallographic domain boundary in the altermagnet ruthenium dioxide (RuO2). Altermagnets are characterized by having a substantial nonrelativistic spin splitting comparable to ferromagnetic materials but with compensated magnetic ordering. The spin splitting originates from the Heisenberg exchange interaction combined with the anisotropic octahedral crystal field from the surrounding nonmagnetic O atoms, which reduces the symmetry relating the two opposite spin sublattices to an antiunitary rotation or mirror symmetry. This introduces a new mechanism for controlling spin-dependent transport phenomena by altering the crystal configuration, specifically through its local chirality, such as the crystal Hall effect. Thus, looking at an interface where the local chirality reverses allowed for a more detailed analysis of how the change of symmetry affects electronic transport. RuO2 was chosen for this study due to its high Néel temperature, metallic nature, and exhibiting one of the largest spin splittings in this new material class. We use first-principle calculations to characterize the interfacial states and their contribution to electronic transport. We observe an induced magnetization at the domain boundary and enhanced anomalous transport along the interface when spin-orbit coupling is considered, due to the change of symmetry. We theorize the localized currents are tunable by the direction of the magnetization at the interface. Our findings will contribute to the understanding of how altermagnetic properties evolve toward interfaces with the reduction in dimensionality and symmetry and contribute to advancements toward the design of sustainable, energy-efficient devices.

### Wednesday Afternoon, November 6, 2024

#### Magnetic Interfaces and Nanostructures Room 121 - Session MI+2D+AC+TF-WeA

#### 2D Magnetism and Magnetic Nanostructures

Moderators: Mikel Holcomb, West Virginia University, Tiffany Kaspar, Pacific Northwest National Laboratory

#### 2:15pm MI+2D+AC+TF-WeA-1 Interface Tunable Magnetism in Transition Metal Telluride Thin Films and Heterostructures, Hang Chi, University of Ottawa, Canada INVITED

Novel quasi-2D magnets are attracting much attention recently. In situ prepared sharp interfaces are desirable for strain engineering and/or hybridizing with other quantum systems, enabling fundamentally new phenomena and opportunities for spintronics [1]. Ferromagnetic Cr<sub>2</sub>Te<sub>3</sub> ultrathin films, optimally grown on Al<sub>2</sub>O<sub>3</sub>(0001) and SrTiO<sub>3</sub>(111) using molecular beam epitaxy, manifest an extraordinary sign reversal in the anomalous Hall conductivity as temperature and/or strain are modulated. The nontrivial Berry curvature in the electronic-structure momentum space is believed to be responsible for this behavior [2]. Furthermore, when proximitized with (Bi,Sb)2Te3-type topological insulator, via the Bloembergen-Rowland interaction, magnetic ordering in monolayer Cr<sub>2</sub>Te<sub>3</sub> is favorably enhanced, displaying an increased Curie temperature [3]. Combining ab initio simulation, advanced scanning tunneling microscopy, magnetic force microscopy, transmission electron microscopy, magneto transport and particularly depth-sensitive polarized neutron reflectometry, Cr<sub>2</sub>Te<sub>3</sub> has been established as a far-reaching platform for further investigating the marriage of magnetism and topology. These findings provide new perspectives to the magnetic topological materials in general, that are topical for the future development of topological spintronics.

#### References

[1] H. Chi and J. S. Moodera, "Progress and prospects in the quantum anomalous Hall effect", APL Mater. 10, 090903 (2022). https://doi.org/10.1063/5.0100989

[2] H. Chi, Y. Ou, T. B. Eldred, W. Gao, S. Kwon, J. Murray, M. Dreyer, R. E. Butera, . . . J. S. Moodera, "Strain-tunable Berry curvature in quasi-twodimensional chromium telluride", Nat. Commun. 14, 3222 (2023). https://doi.org/10.1038/s41467-023-38995-4

[3] Y. Ou, M. Mirzhalilov, N. M. Nemes, J. L. Martinez, M. Rocci, A. Akey, W. Ge, D. Suri, . . . H. Chi, "Enhanced Ferromagnetism in Monolayer  $Cr_2Te_3$  via Topological Insulator Coupling", arXiv:2312.15028 (2024). https://doi.org/10.48550/arXiv.2312.15028

#### Acknowledgment

We acknowledge the support of the Natural Sciences and Engineering Research Council of Canada (NSERC) Discovery Grant RGPIN-2024-06497.

2:45pm MI+2D+AC+TF-WeA-3 AVS National Student Awardee Talk/Falicov Student Award Finalist Talk: Probing Intrinsic Magnetization Dynamics of the Y<sub>3</sub>Fe<sub>3</sub>O<sub>12</sub>/Bi<sub>2</sub>Te<sub>3</sub> Interface at Low Temperature, *A. Willcole*, Sandia National Laboratories, USA; *V. Lauter*, Oak Ridge National Laboratory, USA; *A. Grutter*, National Institute of Standards and Technology (NIST); *C. Dubs*, INNOVENT e.V. Technologieentwicklung, Germany; *D. Lidsky*, Sandia National Laboratories, USA; *Bin Luo*<sup>12</sup>, Northeastern University, US; *M. Lindner*, *T. Reimann*, INNOVENT e.V. Technologieentwicklung, Germany; *N. Bhattacharjee*, Northeastern University, US; *T. Lu*, *P. Sharma*, *N. Valdez*, *C. Pearce*, *T. Monson*, Sandia National Laboratories, USA; Mational Laboratories, USA; M. Bansil, D. Heiman, N. Sun, Northeastern University, US

Topological insulator-magnetic insulator (TI-MI) heterostructures are essential in spintronics, enabling magnetization control via topological surface state-induced spin orbit torque. However, many TI-MI interfaces often face issues like contamination in the magnetic insulator and a lowdensity transitional region in the topological insulator, which obscure the system's intrinsic properties. In this study, we addressed these challenges by depositing sputtered Bi<sub>2</sub>Te<sub>3</sub>(BT) on liquid phase epitaxy grown  $Y_3$ Fe<sub>5</sub>O<sub>12</sub> (YIG)/Gd<sub>3</sub>Ga<sub>5</sub>O<sub>12</sub>. The liquid phase epitaxy grown YIG exhibits exceptional interface quality, without an extended transient layer derived from interdiffusion processes of the substrate or impurity ions, thereby eliminating rare-earth impurity-related losses in the MI at low temperatures. At the TI-MI interface, high resolution depth-sensitive polarized neutron reflectometry confirmed the absence of a low-density transitional growth region of the TI. The demonstrated BT/YIG system is uniquely suited to elucidate the intrinsic TI-magnetic insulator magnetization dynamics due to the lack of an extended transient layer in the magnetic insulator at the magnetic insulator-substrate interface and lack of a low density, intergrowth region of the TI at the TI-magnetic insulator interface.

By overcoming these undesirable interfacial effects, we isolate and probe the intrinsic low-temperature magnetization dynamics and transport properties of the TI-MI interface. Using temperature dependent ferromagnetic resonance (FMR) we found a strong damping enhancement at low temperature due to the topologically protected Dirac surface states (TSS) in the Bi<sub>2</sub>Te<sub>3</sub> film – a signature of significant spin pumping. Accompanying the damping enhancement, we also observed a large induced in-plane magnetic anisotropy for the BT/YIG heterostructure. We explain this by spin-pumping and spin-momentum locking, due to which the precessing spins of the YIG are forced to align with the spins pumped into the TSS and therefore remain locked in the plane of the BT/YIG interface. The temperature dependence of the magnetotransport which supports the suppression of bulk conduction, and the emergence of weakantilocalization is consistent with the low temperature enhanced spin pumping in the BT/YIG that we observed, highlighting the interplay between the transport and spin pumping behavior in the TI-MI system. Further study of TI-magnetic insulator interfaces, specifically magnetic insulators with perpendicular magnetic anisotropy, are pertinent to potentially unlock high temperature quantum anomalous hall effect (QAHE) heterostructures, and the next generation of low power spintronics.

#### 3:00pm MI+2D+AC+TF-WeA-4 Falicov Student Award Finalist Talk: Surface Investigation of ε-phase Mn3Ga on GaN (0001) Substrate using Scanning Tunneling Microscopy, Ashok Shrestha<sup>3</sup>, A. Abbas, D. Ingram, A. Smith, Ohio University

Antiferromagnetic materials have garnered significant attention due to their exotic properties and possible applications in next generation spintronic memory and computing devices [1]. In recent years, research on non-collinear antiferromagnetic materials such as Mn<sub>3</sub>X (X: Ir, Ge, Sn, Ga) has heightened due to non-trivial, topological properties of these materials with unique spin textures [2]. Among these Mn-based antiferromagnets, Mn<sub>3</sub>Ir has been commonly employed for applications [3]. As Ir is an expensive metal, efforts have been made to explore Ir-free antiferromagnets. Particularly, Mn<sub>3</sub>Ga emerges as a promising candidate due to its versatile texture, magnetic ordering, and properties akin to Mn<sub>3</sub>Ir [4]. Among the three distinct phases of Mn<sub>3</sub>Ga, one of the most intriguing yet less explored is the ε-phase (D0<sub>19</sub>-Mn<sub>3</sub>Ga), which exhibits anomalous Hall effect and topological Hall effect in distinct temperature ranges [3]. In this presentation, we will delve into the growth and surface studies of a thin film of D0<sub>19</sub>-Mn<sub>3</sub>Ga on a Ga polar-GaN (0001) substrate.

We have successfully grown an epitaxial ε-phase Mn₃Ga layer using molecular beam epitaxy. The sample quality, lattice constants and crystal structure of the grown film were determined by in-situ reflection high energy electron diffraction and ex-situ X-ray diffraction. Upon examination with scanning tunneling microscopy, the surface revealed multiple terraces and row-like structures. Notably, the edges of the terraces form 120° angles with each other, consistent with the hexagonal crystal structure of the ɛphase Mn<sub>3</sub>Ga. Additionally, we observed several stackings of just a monolayer, with their heights matching the c/2 value of  $Mn_3Ga.$  These measurements are further confirmed by X-ray diffraction. At atomic resolution, hexagonally arranged atoms with a 1 × 1 crystal structure were observed. The measured average in-plane atomic spacing was 5.37 ± 0.05 Å, deviating only -0.56% from theoretical predictions (5.40 Å). However, atomic spacing exhibited local variations. Other interesting structures were also observed in the scanning tunneling microscopy images, which will be discussed in the presentation. Chemical analysis via Rutherford backscattering confirmed the sample's Mn:Ga ratio as 3.2:1.0, which depends on the growth temperature. Further research will involve exploring non-collinear antiferromagnetism using spin-polarized scanning tunneling microscopy, with results to be presented at the conference.

#### References:

5

Chen et al., APL Mater.11, 111026 (2023).

Qin et al., Nature 613(7944), 48 (2023).

Hernandez et al., Surf. and Interface **41**, 103167 (2023).

1. Liu et al., Sci. Rep. **7**(1), 515 (2017).

<sup>3</sup> Falicov Student Award Finalist

### Wednesday Afternoon, November 6, 2024

3:15pm MI+2D+AC+TF-WeA-5 Thermally Generated Spin Transport Across Magnetic Interfaces, Hari Srikanth, USF Tampa INVITED Spin-heat coupling and thermo-spin transport are topical areas of interest for the spintronics community. The origin of longitudinal Spin Seebeck effect (LSSE) and its relationship with magnetic anisotropy as well as magnon propagation across magnetic insulator/heavy metal interfaces have remained challenging issues. LSSE induces incoherent magnon excitations with the application of a temperature gradient across the thickness of a magnetic material. Although the ferrimagnetic insulator  $Y_3Fe_5O_{12}$  (YIG) is known as the benchmark system for LSSE, other members of the insulating rare earth iron garnet family, e.g. the compensated ferrimagnet Gd<sub>3</sub>Fe5O<sub>12</sub> (GdIG), ferrimagnet insulator Tm<sub>3</sub>Fe<sub>5</sub>O<sub>12</sub> (TmIG) etc., are of interest and have received less attention from the point of view of spin-caloritronics. We have pioneered the technique of RF transverse susceptibility to probe the effective magnetic anisotropy in magnetic materials and heterostructures. Combining the RF transverse susceptibility with LSSE measurements, we have shown correlation between bulk and surface anisotropy with the field and temperature dependence of LSSE in YIG/Pt heterostructures and other compensated ferrimagnets like GdIG. Our recent work on TmIG/Pt heterostructures with varying film thickness reveals the clear role of anisotropy and Gilbert damping on the LSSE. From RF susceptibility, LSSE and broadband FMR experiments, quantitative analysis of the magnon propagation length and its correlation with magnetic anisotropy and Gilbert damping has been done. Overall, this talk would present new results in the thermal spin transport of garnet heterostructures which are of fundamental importance in spin transport across magnetic interfaces.

4:15pm MI+2D+AC+TF-WeA-9 Spin Switchable 2D-Superlattice Metal-Halide Perovskite Film via Multiferroic Interface Coupling, Bogdan Dryzhakov, Oak Ridge National Laboratory; B. Hu, University of Tennessee Knoxville; V. Lauter, Oak Ridge Natinal Laboratory

Solution-processible 2D-phase metal-halide perovskites have emerged as a remarkable class of semiconducting, exhibiting a wide-range of optoelectronic properties and multi-functionalities. In this work, interfacing ferromagnetic spins with this semiconductor's Rashba band vields magnetic field control over the excited state spin degrees of freedom, as demonstrated through optical analogues that resolve the spin polarization in steady-state and dynamics, and in-situ neutron scattering methods, where a photo-ferromagnetic profile is depth-resolved. The 2D-superlattice perovskite films are prepared using an optimized, low-cost spin-cast method, resulting in highly crystalline and smooth thin films with a welldefined alternating layered structure of self-assembled organic cations and lead-iodide octahedra. Within the anisotropic 2D-planes of MHPs, fluorinated A-site ligands distort the lattice, yielding robust ferroelectricity and Rashba bands arising from broken inversion symmetry and strong spinorbit coupling. Spin-switchable circularly polarized photoluminescence (CPL) between  $\sigma$ + and  $\sigma$ - polarizations is achieved at the multiferroic perovskite/Co interface by manipulating the ferromagnetic spins on the Co surface between positive and negative magnetic field directions. This switching behavior arises from selective interactions between the ferromagnetic spins on the Co surface and the circularly polarized  $\sigma$ + and  $\sigma$ orbitals within the perovskite's Rashba band structures. Polarized neutron reflectometry measurements reveal long-range interactions of the Co magnetism to the perovskite's spin-polarized excitons, with chemical (NSLD) and magnetization (MSLD) depth profiles indicating optically induced magnetization through the perovskite's thickness. This work presents a fundamental platform for exploring spin selectivity effects within Rashba band structures using CPL studies in multiferroic perovskite/ferromagnetic interfaces.

4:30pm MI+2D+AC+TF-WeA-10 Engineering the Hybrid Nanocolumnar Metamaterial Platforms for Advanced Optical and Magnetic Applications, Ufuk Kilic, C. Briley, University of Nebraska-Lincoln; R. Feder, Fraunhofer Institute for Microstructure of Materials and Systems, Germany; D. Sekora, University of Nebraska-Lincoln; A. Ullah, University of Nebraska - Lincoln; A. Mock, Weber State University; C. Binek, University of Nebraska - Lincoln; H. Schmidt, Friedrich Schiller University, Germany; C. Argyropoulos, The Pennsylvania State University; E. Schubert, M. Schubert, University of Nebraska - Lincoln

The hybrid metamaterial platforms have garnered remarkable attention in various subdiciplines of physics, chemisty, and biology due to their wide range of advanced functionalities including strong tunable optical and magnetic anisotropies, the ability to confine, modulate, and control of light, to engineer new permanent nanomagnets, for example. In this study, we employed a custom-built ultra-high vacuum electron-beam glancing angle deposition technique [1] to fabricate spatially-coherent, super lattice type

nanocolumnar heterostructure metamaterial platforms from both hard (cobalt) and soft (permalloy) magnetic materials. Furthermore, by using atomic layer deposition technique, we incorporate ultrathin interface layer ( $^{-1.4}$  nm) of Al<sub>2</sub>O<sub>3</sub> between the magnetic nano-columnar subsegments. This interface engineering at nanoscale provides another angle of freedom to tune both the magnetic and optical properties of hybrid nanocolumnar metamaterial platforms.

By taking the advantage of the generalized spectroscopic ellipsometry technique, we reached out the complex anisotropic dielectric properties of the fabricated structures. Our analysis involves widely used anisotropic Bruggeman effective medium model approach which provides to extract optical and structural properties, accordingly [2]. Moreover, to perform magnetic characterization of our fabricated metamaterial design, we employed both generalized vector magneto-optic ellipsometry and vibrating sample magnetometer measurements [3]. In order to delve into the fundamental driving mechanisms behind the anisotropic tunable magneto-optic responses from the proposed metamaterial platforms, we conducted a series of systematic micromagnetic and finite element modeling simulations, as well. We believe that these new structural metamaterial designs can result in the development of next-generation sensing devices, permenant nanomagnets, magnetic recording technologies, on-chip nanophotonic and opto-magnetic device applications. References:

[1] Kilic, U., et al. Sci Rep 9, 71 (2019).

[2] Schmidt, D., and Schubert, M., J. Appl. Phys. 114.8 (2013).

[3] Briley, Chad, et al. Appl. Phys. Lett. 106.13 (2015).

4:45pm MI+2D+AC+TF-WeA-11 Magnetic Field Affects Oxygen Evolution Reaction Only in Metal Oxy-Hydroxides, Filippo Longo, Chemical Energy Carriers and Vehicle Systems Laboratory, Empa, Swiss Federal Laboratories for Materials Science and Technology, Switzerland; R. Peremadathil Pradeep, E. Darwin, H. Huq, Magnetic and Functional Thin Films Laboratory, Empa, Swiss Federal Laboratories for Materials Science and Technology, Switzerland; A. Borgschulte, Chemical Energy Carriers and Vehicle Systems Laboratory, Empa, Swiss Federal Laboratories for Materials Science and Technology, Switzerland

Ni-based electrodes have been largely employed in alkaline electrolyzers for the production of H<sub>2</sub> and O<sub>2</sub> [1]. Due to the sluggish kinetics of the oxygen evolution reaction (OER), many experimental approaches have been employed to boost the catalytic performance of such electrodes [2]. The application of an external magnetic field during OER has shown outstanding catalytic improvement [3]. Despite considerable research effort, the understanding of its origin is still object of debate [4,5]. In this work we show how the Ni-based electrodes improve their catalytic activity towards OER during the application of an external magnetic field. We investigate in detail the catalytically active surface, the microscopic, electronic, and magnetic structures by soft- and hard X-ray photoelectron spectroscopy combined with impedance spectroscopy and magneto-optical measurements. It is relevant in this context that the oxy-hydroxide formed during OER is the catalytically active compound, and is thus likely also the origin of the magnetic effect. To underline the importance of the oxyhydroxide formation, we employ a multilayered system made of Co-Pt-Ru multi-lattices, exhibiting much more favorable magnetic properties (such as strong perpendicular magnetic anisotropy) than nickel. Interestingly, hardly any improvement of OER is found. The various findings corroborate the picture of spin-exchange interaction of metal-oxide bonds as the underlying mechanism of the magneto-chemical effect.

[1] S. W. Sharshir et al., International Journal of Hydrogen Energy (2023).[2] J. S. Kim et al., Adv. Energy Mater. (2018), 8, 1702774.[3] F.A. Garcés-Pineda et al., Nat Energy 4, 519-525 (2019).[4] T. Wu et al., Nat Commun 12, 3634 (2021).[5] X. Ren et al., Nat Commun 14, 2482 (2023).

### Thursday Morning, November 7, 2024

#### Actinides and Rare Earths Room 123 - Session AC+MI-ThM

### Superconductivity, Electron Correlation, Magnetism and Complex Behavior

Moderators: Tomasz Durakiewicz, Idaho National Laboratory, Ladislav Havela, Charles University, Czech Republic, David Shuh, Lawrence Berkeley National Laboratory, James G. Tobin, University of Wisconsin-Oshkosh

#### 8:00am AC+MI-ThM-1 Electronic Structures of f-Electron Superconductors,

Shin-ichi Fujimori, Japan Atomic Energy Agency, JapanINVITEDThe unconventional superconductors in f-based materials attract muchattention in recent years. In the present talk the electronic structures of f-electron superconductors UTe2 and Celr3 will be presented.

Recently, it was discovered that UTe<sub>2</sub> has relatively high transition temperature ( $T_c$ =2.1 K), and it is classified into one of such class of materials [1,2]. The electronic structure of UTe<sub>2</sub> was studied by resonant photoelectron spectroscopy (RPES) and angle-resolved photoelectron spectroscopy (ARPES) with soft X-ray synchrotron radiation [3]. The partial U 5*f* density of states of UTe<sub>2</sub> were imaged by the U 4*d*-5*f* RPES and it was found that the U 5*f* state has an itinerant character, but there exists an incoherent peak due to the strong electron correlation effects. The band structure of UTe<sub>2</sub> was obtained by ARPES and its overall band structure was mostly explained by band structure calculations, except for the incoherent band at  $E_B$ ~0.5 eV. These results suggest that the U 5*f* states of UTe<sub>2</sub> have itinerant but strongly-correlated nature.

The electronic structure of the *f*-based superconductor CeIr<sub>3</sub> ( $T_{sc}$ =3.1 K) was also studied by photoelectron spectroscopy [4]. The energy distribution of the Ce 4*f* states were revealed by the Ce 3*d*-4*f* RPES. The contribution of the Ce 4*f* states to the density of states (DOS) at the Fermi energy was estimated to be nearly half of that of the Ir 5*d* states, implying that the Ce 4*f* states have a considerable contribution to the DOS at the Fermi energy. These results suggest that CeIr<sub>3</sub> is an *s*-wave-type superconductor with a considerable contribution from the Ce 4*f* states.

Work performed in collaboration with Ikuto Kawasaki, Yukiharu Takeda, Hiroshi Yamagami, Norimasa Sasabe, Yoshiki J Sato, Ai Nakamura, Yusei Shimizu, Arvind Maurya, Yoshiya Homma, Dexin Li, Fuminori Honda, and Dai Aoki.

#### References

[1] S. Ran et al., Science 365, 684 (2019).

[2] D. Aoki et al., J. Phys. Soc. 88, 043702 (2019).

[3] S. Fujimori, et al., J. Phys. Soc. Jpn. 88, 103701 (2019).

[4] S. Fujimori et al., Electron. Struct. 5, 045009 (2023).

8:30am AC+MI-ThM-3 RIXS Study of the 5f Configuration in UTe2: Low-Energy Excitations, Te2 Chains and U Dimers, D. Christovam, M. Sundermann, A. Marino, Max Planck Institute for Chemical Physics of Solids, Germany; H. Gretarsson, PETRA III, Deutsches Elektronen-Synchrotron DESY, Germany; B. Keimer, Max Planck Institute for Solid State Research, Germany; A. Gloskovskii, PETRA III, Deutsches Elektronen-Synchrotron DESY, Germany; M. Haverkort, Institute for Theoretical Physics, Heidelberg University, Germany; I. Elfimov, University of British Columbia, Canada; E. Bauer, P. Rosa, Los Alamos National Laboratory; A. Severing, Institute of Physics II, University of Cologne, Germany; Liu Hao Tjeng, Max Planck Institute for Chemical Physics of Solids, Germany INVITED UTe<sub>2</sub> is a recently discovered odd-parity superconductor, emerging as a promising candidate for topological superconductivity [1-3]. A key challenge in understanding its anisotropic properties and their dependence on tuning parameters is finding the appropriate Ansatz for describing such a complex electronic system, situated at the border between localization and itinerancy. It is essential to determine the extent to which local physics persists and to identify the governing electronic f<sup>n</sup> configuration. Although the latter has been addressed using various methods, a fierce debate remains about whether the main configuration is  $f^2$  or  $f^3$ .

Discrepancies in determining the dominant  $f^n$  configuration are common in uranium-based intermetallics. We argue that this apparent contradiction arises from the challenge of accurately analyzing the spectra, given the complexity associated with the underlying many-body problem and uncertainties in the input model parameters.

In our study, we opt for a newly developed spectroscopic method for U materials, namely resonant inelastic x-ray scattering (RIXS) in the tender x-ray range [4]. Applying this method to UTe<sub>2</sub>, we can unambiguously detect the presence of atomic-like U 5*f*-5*f* low-energy excitations. This establishes the correlated nature of UTe<sub>2</sub> despite the presence of strong covalence and band formation. Moreover, we can also fingerprint the U 5*f*<sup>2</sup> as the main configuration without the need to rely on accurate calculations, thus settling the debate about the 5*f* valence state [5].

The short Te2-Te2 distances, however, seem incompatible with a formal U<sup>4+</sup> valence. We resolve this puzzle by utilizing band structure calculations and photon energy-dependent photoemission. We found that the charge transfer from the  $5p_{Y||b}$  band of the Te2 chain is directed not to the U 5*f* but to the bonding state of the U  $6d_{3z2+z2}$  orbitals of the U dimer. Notably, these two band states are non-bonding to each other or to other non-5*f* states in the material. Yet, both bands hybridize with the U 5*f*, emphasizing that the description of the physical properties of UTe<sub>2</sub> must include the Te2  $5p_{Y||b}$  and U  $6d_{3z2+z2}$  bands plus the  $5f^2Ansatz$  [5] These are all very peculiar findings, making UTe<sub>2</sub> a very special material indeed.

[1] S. Ran et al., Science, **365**(6454), 684–687 (2019).

[2] D. Aoki et al., J. Phys. Soc. Jpn. 88(4), 043702 (2019)

[3] for recent review: S.K. Lewin *et al.*, Rep. Prog. Phys. **86**(11):114501, 2023.

[4] A. Marino et al., Phys. Rev. B 108, 045142 (2023)

[5] D. S. Christovam *et al.*, arXiv 2402.03852 [https://arxiv.org/abs/2402.03852] (2024)

9:00am AC+MI-ThM-5 Incommensurate Antiferromagnetism in UTe<sub>2</sub> Under Pressure, *William Knafo*, LNCMI, CNRS, France INVITED The discovery of multiple superconducting phases in UTe<sub>2</sub> boosted research on correlated-electron physics [1,2,3,4]. The proximity to a ferromagnetic quantum phase transition was initially proposed as a driving force to tripletpairing superconductivity [1], and this heavy-fermion paramagnet was rapidly identified as a reference compound to study the interplay between magnetism and unconventional superconductivity with multiple degrees of freedom.

Here, we present neutron diffraction experiments showing that long-range incommensurate antiferromagnetic order is established in UTe<sub>2</sub> under pressure [5]. The propagation vector  $\mathbf{k}_m = (0.07, 0.33, 1)$  of the observed antiferromagnetic phase is close to a wavevector where antiferromagnetic fluctuations have previously been observed at ambient pressure [6,7]. Our work shows that superconductivity in UTe<sub>2</sub> develops in the vicinity of a long-range antiferromagnetic phase, which differs from the initial proposition of a nearby ferromagnetic phase. The nearly-antiferromagnetic nature of UTe<sub>2</sub> at ambient pressure and its relationship with superconductivity will be discussed.

This work was done in collaboration with T. Thebault, P. Manuel, D. Khalyavin, F. Orlandi, E. Ressouche, K. Beauvois, G. Lapertot, K. Kaneko, D. Aoki, D. Braithwaite, G. Knebel, and S. Raymond.

[1]	Ran	e	et	al.,	Science	:	365,	684	(2019).
[2]	Knebel	et	al,	J. Phy	s. Soc.	Jpn.	88,	063707	(2019).
[3]	Braithv	vaite	et	al.,	Commur	i. Pł	iys.	<b>2</b> , 147	(2019).
[4]	Ran	et	al.,	Nat.	Phys.	15,	12	50–1254	(2019).
[5]	Knafo			et a		al.,	al., arXiv:231		1.05455.
[6]	Duan	et	al.,	Phys.	Rev.	Lett.	125,	237003	(2020).
[7]	Knafo	et	al.,	Phys.	Rev.	В :	104,	L100409	(2021).

9:30am AC+MI-ThM-7 New Spectroscopic Insights into Correlation Effects and Covalency of U 5f Electrons in Uranium Intermetallic Compounds, A. Marino, M. Sundermann, D. Christovam, Max-Planck Institute for Chemical Physics of Solids, Physics of Correlated Matter, Dresden, Germany; H. Gretarsson, DESY/PETRA-III, Hamburg, Germany; B. Keimer, Max-Planck Institute for Solid State Research, Stuttgart, Germany; A. Gloskovskii, DESY/PETRA-III, Hamburg, Germany; J. Kunes, Department of Condensed Matter Physics, Masaryk University, Brno, Czechia; A. Hariki, Department of Physics and Electronics, Osaka Metropolitan University, Osaka, Japan; L. Tjeng, Max-Planck Institute for Chemical Physics of Solids, Physics of Correlated Matter, Dresden, Germany; Andrea Severing, Institute of Physics II, University of Cologne, Cologne, Germany Uranium intermetallic compounds exhibit a wide range of fascinating physical phenomena that arise from the intricate interplay between atomic-

### Thursday Morning, November 7, 2024

like correlations and band formation of the U 5*f* electrons. Describing their electronic structure is a challenge, particularly as atomic-like states have remained experimentally inaccessible. Ongoing disputes revolve around the existence of atomic-like states and, if present, around determining which configuration—U 5*f*<sup>3</sup> or U 5*f*<sup>2</sup>—provides the Ansatz or starting point for describing the low-energy properties. Furthermore, these correlated compounds exhibit strong intermediate valency, fuelling intense debates about the actual filling of the 5*f* shell and the degree of covalency.

This presentation introduces two novel and complementary methods: (1) valence band resonant inelastic x-ray scattering (RIXS) using tender x-rays and (2) photon energy-dependent photoelectron spectroscopy (PES & HAXPES) in combination with DFT+DMFT calculations.

(1) Valence Band RIXS: Using high-resolution RIXS at the U M-edges (3.5-3.7 keV), we observe low-energy excitations originating from atomic-like multiplet interactions [1]. The excellent signal-to-background ratio and the multiplet structure serve as a unique fingerprint for the U  $5f^{\text{fn}}$  configuration involved, offering clear evidence of the presence of local correlation physics. This method unambiguously determines the dominating configuration [1].

(2) Combination of DFT+DMFT calculations with soft and hard x-ray photoemission (PES & HAXPES): The energy dependencies of the photoionization cross-sections allow for the disentanglement of correlated 5f from band-like non-5f spectral contributions, enabling reliable tuning of parameters such as Hund's-J, Hubbard- $U_{ff}$ , and, most importantly, the double counting correction (m<sub>dc</sub>) to reproduce valence band spectra. We applied this method to UGa<sub>2</sub> and UB<sub>2</sub>, two model materials representing the extreme ends of the localization-delocalization range. Despite their vastly different properties, we found the mean 5f shell filling to be almost contributing to the ground state differs significantly: narrow in 'localized' UGa<sub>2</sub> and almost statistically broad in 'itinerant' UB<sub>2</sub>. This method also reproduces the satellites in the 4f core-level spectra and explains the presence/absence of 5f-5f-multiplet excitations in the RIXS spectra [2].

[1] A. Marino *et al.* Phys. Rev. B, **108** (2023) 045142 [2] A. Marino, A. Hariki *et al.*, to be published

11:00am AC+MI-ThM-13 Isotopic Fingerprinting in Nuclear Forensics: Leveraging Aerogel and LEXAN® SSNTD for Enhanced Analysis, *R. Babayew, Itzhak Halevy, N. Elgad, Y. Yehuda-Zada,* Ben Gurion Uni., Israel; J. Lorincik, Research Centre Řež, Czech Republic, Israel; *M. Last, I. Orion, G. Katarivas-Levy,* Ben Gurion Uni., Israel; *A. Weiss,* Faculty of Engineering, Bar Ilan University, Israel

In nuclear forensics, ensuring the reliability and accuracy of the analysis is paramount. Traditional methods rely heavily on the expertise of trained researchers, leading to variations in results. To address this challenge, we present innovative techniques aimed at automating Fission Track Analysis through advanced image processing algorithms applied to microscope images.

Our research introduces a pioneering approach that leverages Monte Carlo simulations, particularly utilizing the GEANT4 software, to generate synthetic models of fission tracks. By simulating various physical parameters such as thermal neutron flux, fission cross-section, particle size, and radiation time, our Trainer2 software accurately calculates fission tracks on our Lexan detector, producing results akin to real-world scenarios.

Moreover, our methodology integrates trajectory data from the fission products trajectory database, derived from GEANT4 simulations, to generate synthetic models closely resembling actual microscope images. This synthetic bank of images serves as a controlled and versatile dataset for the development of robust image analysis tools. These tools aim to automate the identification of fission track clusters, thus eliminating the need for manual intervention and minimizing the likelihood of human errors.

Our preliminary software for image processing demonstrates promising efficacy in detecting fission track clusters, providing a comprehensive record of fission sites for analysis. By identifying the length of tracks and their distribution, we can determine the source isotope and the density of impurities, thus advancing our understanding of nuclear materials.

Additionally, the software calculates the number of tracks, enhancing the efficiency of data interpretation.

Furthermore, we introduce a novel approach utilizing penetrating fluorescent colors for 3D scanning of detectors, enhancing our ability to investigate fission track stars beyond mere projections.

In conclusion, our research underscores the importance of automating FTA for nuclear safeguards, aiming to minimize human intervention while fortifying the precision and efficiency of nuclear investigations. Through the seamless integration of GEANT4 simulations and advanced image processing algorithms, we envision a future where nuclear forensic analysis is more reliable, accurate and streamlined.

Keywords: Nuclear forensics, Fission Track Analysis, Monte Carlo simulations, GEANT4, Image processing algorithms, Automated analysis, nuclear safeguards.

#### References

[1]Rami Babayew *et al.*, Simulation tools for improvement of the fission track analysis method for nuclear forensics (2024), JRNC, 10.1007/s10967-023-09313-5

11:15am AC+MI-ThM-14 Unusual orders in the heavy-fermion superconductor CeRh<sub>2</sub>As<sub>2</sub>, Gertrud Zwicknagl, TU Braunschweig, Germany The heavy-fermion compound CeRh2As<sub>2</sub> exhibits a complex phase diagram with rather unusual states at low temperatures. A prominent example is multi-phase superconductivity[1] which seems to develop inside a normal state characterized by itinerant multi-polar order. The present talk focusses on the instabilities of the strongly renormalized Fermi liquid state in the heavy-fermion compound CeRh2As2. The central focus is the role played by the non-symmorphic lattice structure and the consequences of the Crystalline Electric Field (CEF) which removes the orbital degeneracy of the Ce 4f states. The narrow quasiparticle bands which arise from the Ce-4f degrees of freedom via the Kondo effect are calculated by means of the Renormalized Band (RB) method. We conjecture that the quasi-quartet CEF ground state in combination with pronounced nesting features of the Fermi surface may give rise to ordered states involving multipolar degrees of freedom [2].

#### References

1.

S. Khim et al., Science 373, 1012 (2021)

2. RevX 12, 011023 (2022)

11:30am AC+MI-ThM-15 Thermoelectric Properties of Strongly Correlated Compounds NpPd<sub>3</sub> and PuPd<sub>3</sub>, *Krzysztof Gofryk*, Idaho National Laboratory; *J. Griveau*, 3DG Joint Research Centre, Directorate G-Nuclear Safety and Security, Germany; *K. McEwen*, University College London, UK; *W. Nellis*, Harvard University; *J. Smith*, Los Alamos National Laboratory

Actinides are characterized by the coexistence of localized and itinerant (delocalized) 5f-states near the Fermi energy. This dual nature of the 5f electrons leads to many exotic phenomena that are observed in these strongly correlated materials, spanning magnetic ordering, heavy-fermion ground state, unconventional superconductivity, and/or a "non-Fermi liquid" state. The unusual transport properties of the strongly correlated electron systems are related to the formation, near the Fermi level, of a narrow band with a large density of states. Therefore, the Seebeck coefficient in these materials, being proportional to the density of states at the Fermi level, often reaches large values and shows the characteristic temperature dependence [Phys. Rev. B 94, 195117 (2016)]. To explore the influence of electronic correlations on the transport properties in the AnPd<sub>3</sub> system, here we present low-temperature electrical resistivity and Seebeck coefficient measurements of NpPd<sub>3</sub> and PuPd<sub>3</sub> intermetallics. We show that the electrical resistivity shows characteristic behavior of systems with Kondo interactions. The magnitude and overall temperature dependence of the thermoelectric power of NpPd3 and PuPd3 are characteristic of 4f- and 5f-electron strongly correlated materials. For cubic NpPd<sub>3</sub> a sharp transition and change of sign in S(T) at the Néel temperature indicate a first-order nature of the magnetic transition, probably accompanied by a large change in the Fermi surface topology. We have also estimated the power factor  $(S^2/\rho)$  of these materials.

### Thursday Afternoon, November 7, 2024

#### Actinides and Rare Earths Room 123 - Session AC+MI-ThA

#### Forensics, Disposal and Pu

Moderators: Itzhak Halevy, Ben Gurion Uni. Be'er Sheva, Alison Pugmire, LANL, Paul Roussel, AWE

2:15pm AC+MI-ThA-1 A New Approach for Nuclear Forensics Investigations of Uranium Dioxide : Application of Laboratory Based Photoelectron Spectroscopy with Hard and Soft X-ray Sources, Stuart Dunn, P. Roussel, AWE, UK; A. Wood, B. Spencer, R. Harrison, University of Manchester, UK; P. Kaye, M. Higginson, AWE, UK; W. Flavell, University of Manchester, UK INVITED

Nuclear Forensic investigations rely on the analysis of the chemical and physical properties to determine the provenance of nuclear materials, found out of regulatory control. X-ray photoelectron spectroscopy (XPS) has been shown to be a powerful tool in supporting material assessment by analysis of the top few nanometres of the surface. With the onset of laboratory based hard x-ray photoelectron spectroscopy (HAXPES) instrumentation, this provides the opportunity to probe deeper into the bulk. Furthermore, HAXPES spectra of high Z elements will have multiple core level peaks occurring over a range of different depths and analysis of these can offer a unique non-destructive depth profile. The work presented in this study demonstrates the utility of a combined XPS and HAXPES analysis to isolate forensic signatures on the surface and into the bulk of uranium dioxide. Survey quantification shows the changing stoichiometry, utilising a 9.25 KeV excitation range of HAXPES, from different average depths within the sample matrix. Peak fitting of high-resolution spectra allows identification of oxidation states as well inspection of secondary features, which provide insight into the material characteristics. Combined with XPS analysis, this shows different chemical and elemental states at the surface into the bulk sample, highlighting the usefulness of this approach. QUASES-Tougaard analysis was performed to determine the in-depth distribution of atoms, developing a consistent model to describe the surface overlayer, correlated to the chemical and stoichiometric differences over the excitation range. Finally, the MNN X-ray excited Auger electron spectra are acquired from uranium dioxides for the first time for use in the application of a Wagner or chemical state plot. This study is the first in a series of analysis campaigns on uranium bearing materials.

#### 2:45pm AC+MI-ThA-3 Making Use of X-ray Emission Signatures in the Scanning Electron Microscope to understand f-Element Speciation and Phase, Mark Croce, Los Alamos National Laboratory INVITED

While X-ray absorption spectroscopy is exquisitely sensitive to signatures of chemical speciation and phase, what if similar information could be obtained from the scanning electron microscope? Scanning electron microscopes have become more than imaging tools - they are accessible microanalysis platforms with nanoscale spatial resolution and are compatible with a wide variety of samples including those not suitable for X-ray absorption spectroscopy. Although the physics relating the chemical and physical state of an atom to X-ray emission is more complex than for Xray absorption, there are still distinct signatures present in the X-ray emission spectra. The twofold challenge is to measure them and interpret them. Recent development in low-temperature microcalorimeter spectrometers has made it possible to simultaneously achieve the energy resolution and detection efficiency needed to observe this fine structure in X-ray emission resulting from the interaction of the microscope's electron beam with a sample. In parallel, extending molecular and atomic theory to interpret X-ray emission spectra is beginning to allow use of this capability as a research tool to determine chemical speciation and phase for felements including cerium, uranium, and plutonium even in non-ideal samples. We present progress towards developing what we call "Hyperspectral X-ray Imaging" using a large-array microcalorimeter X-ray spectrometer with <10 eV FWHM energy resolution at 3 keV coupled to a commercial scanning electron microscope, recent results on lanthanide and actinide samples, and future applications of the method to support felement LA-UR-24-21795 science.

3:15pm AC+MI-ThA-5 Automated Particle Analysis of Actinide-Bearing Nuclear Wastes, *Edgar Buck*, Pacific Northwest National Laboratory

Automated particle analysis (APA) is performed on the Scanning Electron Microscope/X-Ray Energy Dispersive Spectroscopy (SEM-EDS) and enables the characterization of morphology and composition of particles. This method allows hundreds to thousands of particles to be examined and reduces operator bias. We have applied APA methods to radioactive Hanford tank waste materials containing rare earth elements, uranium, and plutonium. The challenge for APA with highly heterogeneous materials is the variability in particle size. An important component of the APA is the preparation of the samples for analysis and the segmentation routines used to locate particles of interest. Biased results can be generated during the deposition of particles with larger particles tending to fall out more quickly than smaller particles, and therefore can become concentrated at the center of the sample stub, where the material is directly pipetted. It is important to be aware of the factors controlling the deposition of the particles and analyze the entire SEM stub to obtain representative data. Image segmentation routines have to be calibrated to prevent missing particles and for obtaining accurate morphological data. In this presentation, we will describe the efforts to characterize and classify the actinide-rich wastes.

3:30pm AC+MI-ThA-6 Development of X-Ray Spectromicroscopy Techniques for Nuclear Safeguards and Nuclear Forensics, David Shuh, A. Ditter, N. Cicchetti, O. Gunther, LBNL; J. Brackbill, UC Berkeley/LBNL; R. Lim, A. Baker, S. Donald, B. Chung, LLNL; R. Coles, BNL; A. Duffin, J. Ward, M. Miller, PNNL

The on-going development of improved characterization methods and signatures is crucial to ensure that nuclear safeguards and forensics activities remain effective. For these purposes, the development of X-ray techniques is particularly useful because of their elemental specificity and non-destructive nature that could enable a first-in capability. Tunable synchrotron radiation X-ray approaches provide a means to extend the scope of safeguards and forensics investigations in elemental, chemical, and structural analysis which can be done in imaging modes that in some cases, reaches to the nanoscale. The ability to use tunable, focused X-ray beams makes synchrotron radiation sources a potentially disruptive tool for addition into the array of characterization techniques currently employed, particularly for the investigation of particles or areas of interest in smaller specimens possessing bulk-like characteristics. However, the use of synchrotron radiation methods also presents some unique challenges for the implementation of safeguards and forensic efforts at the synchrotron radiation facility sites (ALS, APS, NSLS-2, and SSRL). Synchrotron radiationbased safeguards and forensics studies over the past several years conducted at nearly all of the U.S. Dept. of Energy synchrotron radiation user facilities throughout the X-ray spectrum have furthered this case, as well as clearly identifying areas that require improvement. At the same time, there have been significant performance improvements in fixedenergy laboratory-based X-ray instrumentation suitable for contemporary, spatially-resolved safeguards and forensics (primarily XRF) studies. Additionally, there have been continued efforts and strides made towards the realization of true laboratory-based X-ray light sources that could provide competitive X-ray flux and tunability, albeit in the future, that might provide the best combination of performance and characteristics necessary for safeguards and forensics characterization activities. A current assessment of the relative strengths and drawbacks of the respective X-ray approaches, as well as a performance comparison will be presented, leading into an overall the future outlook in terms of safeguards and forensics.

3:45pm AC+MI-ThA-7 Site-Specific and Spatially Resolved Morphological and Chemical Analysis of Plutonium and Uranium Materials, Brandon Chung, A. Baker, S. Donald, T. Li, R. Lim, U. Mehta, D. Rosas, D. Servando-Williams, N. Cicchetti, Lawrence Livermore National Laboratory; A. Ditter, O. Gunther, D. Shuh, Lawrence Berkeley National Laboratory Nuclear forensics requires accurate identification of distinguishing material characteristics to delineate the material's origin-to-interdiction information. Morphological and chemical variation in nuclear materials over large scales of observation can provide valuable information that can assist interpretation of the material's varying provenance, process, and pathways. We will describe our efforts to strengthen operational and scientific methodologies to employ the focused ion beam-scanning electron microscopy (FIB-SEM) on uranium (U) and plutonium (Pu) materials for internal morphological analysis including site-specific 3D microscopy and spatially resolved characterizations of material features using transmission electron microscopy (TEM) and X-ray synchrotron spectromicroscopy. Both U and Pu materials show variations in the internal chemical composition and morphology from their production processes and storage environments. This information is of potential use in discriminating material signals to identify the origin and history of interdicted nuclear materials.

### Thursday Afternoon, November 7, 2024

4:00pm AC+MI-ThA-8 An Entropic Approach to Estimating Orbital Occupancies in Plutonium, *Miles Beaux*, Los Alamos National Laboratory Janoschek, et al. described the ground state of plutonium (Pu) as being "governed by valence fluctuations, that is, a quantum mechanical superposition of localized and itinerant electronic configurations." [*Science Advances*, 1, 6 (2015)]. By representing this ground state generally as

#### $[Rn]7s^{2+\gamma s,Pu}5f^{6+\gamma f,Pu}6d^{0+\gamma d,Pu}7p^{0+\gamma p,Pu}$

where  $\gamma_{s,Pu}, \gamma_{f,Pu}, \gamma_{d,Pu}$ , and  $\gamma_{p,Pu}$  represent potentially non-integer deviations from the integer occupancies of their respective orbitals, a combinatorial approach can be applied to the allowable permutations of quantum electronic configurations as a means of describing the electron degrees of freedom. This approach enables a classical statistical mechanics methodology to be applied to the discrete quantum states for conceptualizing and investigating the multiconfigurational ground state of Pu. Specifically, an over-approximation (with Hund's rule relaxed) and an under-approximation (with Hund's rule enforced) of electronic structure entropy has been established for varying ranges of potentially near energy degenerate occupancy configurations for plutonium. This bracketing of electronic structure entropy is compared with the known molar entropy of Pu to narrow down the set of possible localized and itinerant electronic configurations that can reasonably contribute to the quantum mechanical superposition of Pu's multiconfigurational ground state, as well as to estimate the non-integer orbital occupancies of its 7s-, 5f-, 6d- and 7porbitals.

#### LA-UR-24-22282

### 4:15pm AC+MI-ThA-9 The Problem with the Second Derivative Method in EELS\*, *JG Tobin*, University of Wisconsin-Oshkosh

The second derivative mode of peak analysis in electron energy loss spectroscopy (EELS) in a Transmission Electron Microscope (TEM) has been quantitatively evaluated in terms of the accuracy of the method.\*This includes a demonstration of the importance of the second derivative peak width, the second order dependency of the accuracy upon that peak width and effect of high frequency noise in the spectra.It was found that, while EELS does converge to an X-ray Absorption Spectroscopy (XAS)-like limit (electron dipole transition) at high energies, there are significant issues with the 2<sup>nd</sup> Derivative Model.

- 1. There is no fixed relationship between non-derivative peak intensities and 2<sup>nd</sup> derivative peak intensities.Changing peak-shapes changes the ratio.
- Assuming that peak-shapes remain constant, which may not be justified, there is a second order dependence of the ratio upon the peak width of the 2<sup>nd</sup> Derivative peak.
- The second order dependence upon the peak width manifests itself in two very distinct ways: with random errors and systematic errors.
- 1. The random error from high frequency noise places a limit on the number of significant digits in the BR result.
- The systematic error has shown up in the BR predictions and 5f population estimates (n) for the localized systems Pu, PO<sub>2</sub> and UO<sub>2</sub>.

The 2<sup>nd</sup> Derivative Mode in EELS should be used with great caution in quantitative BR analyses of 5f populations.

\*J. G. Tobin, "A quantitative evaluation of the 2nd derivative mode in electron energy loss spectroscopy," J. Electron Spectroscopy Rel. Phen. 268, 147387 (2023), https://doi.org/10.1016/j.elspec.2023.147387

### Thursday Evening, November 7, 2024

#### **Magnetic Interfaces and Nanostructures Room Central Hall - Session MI-ThP**

#### **Magnetic Interfaces and Nanostructures Poster Session**

MI-ThP-1 Molecular Beam Epitaxy of Antiferromagnetic Kagome Alloy CrSn on LaAlO3 (111), Tyler Erickson, Ohio University; S. Upadhyay, Oak Ridge National Laboratory, USA; H. Hall, A. Shrestha, A. Abbas, Ohio University; S. Rajasabai, Vellore Institute of Technology, India; D. Ingram, S. Kaya, Ohio University; U. Kumar, Vellore Institute of Technology, India; A. Smith, Ohio University; D. Russell, F. Yang, Ohio State University

Antiferromagnetic Kagome materials with topologically non-trivial electronic structure provide hosts for exotic magnetic phenomena that is useful for spintronic devices [1-3]. The localization of spin states within the Kagome layers provides opportunities for creating quantum spin-liquid ground states [1], and the capability of tuning the Berry curvature near the Weyl points, thereby engineering moment orientations which could lead to large anomalous Hall effects [2], give these materials a bright future in spintronic devices.At present, we are exploring the possibility of CrSn as a future candidate. Rajasabaiet al.recently published introductory work suggesting an antiferromagnetic Kagome crystal structure for CrSn with spin orientations aligned coplanar and anti-aligned between planes [3]. We have attempted to grow this CrSn alloy using molecular beam epitaxy and to compare it to the expected structure predicted by theory. We have grown multiple CrSn samples and investigated their crystallographic structures and magnetic properties through reflection high-energy electron diffraction, xray diffraction, atomic force microscopy, and superconducting quantum interference devicemeasurements. Our RHEED measurements give an inplanelattice parameter of 5.33 ± 0.17 Å while XRD measurements give an out-of-plane dspacing of 2.19 ± 0.02 Å and thereforean out-of-planelattice parameter of 4.38 ± 0.02 Å. These lattice parameters are in good agreement with the predicted lattice parameters. Furthermore, SQUID measurements confirm the lack of ferromagnetism and suggest possible antiferromagnetism.

This research has been supported by the U.S. Department of Energy, Office of Basic Energy Sciences, Division of Materials Sciences and Engineering under Award No. DE-FG02-06ER46317.

[1]S. Li,Y. Cui, Z. Zeng, et al., Phys. Rev. B109, 104403 (2024).

[2]L. Song et al., Advanced Functional Materials 2316588 (2024).

[3]S. Rajasabai and U. Koppolu, Journal of Superconductivity and Novel Magnetism 35, 839 (2022).

#### MI-ThP-3 Interactions of Extended Magnetic Defects in Semimetallic Systems, Samuel Tkacik, E. Thareja, J. Gayles, University of South Florida

Topological semimetals offer a unique opportunity to produce controllable magnetic states and intrinsic spin currents that are robust against backscattering from most types of disorder or defects. This is due to nominal protection offered by the topology of their electronic structure. In this work we study extended magnetic defects in models of semi-metallic structures and examine interactions that arise from the magnetic and electrostatic potentials that characterize these defects. We use scattering theory with a conserved current to study the interactions between extended defects and the bulk with parameters motivated from firstprinciple calculations of Dirac semimetals. We show that two different regimes exist for a finite and discrete model depending on whether the lattice width is odd or even. We study similarities and differences between bound states in both regimes. Our modelled system is expansive in that it uses parameters derived by first-principle calculations and therefore directly motivates experimental studies in such topological systems. Furthermore, our modelled system serves as a fundamental framework for novel devices with magnetic defects.

#### MI-ThP-4 Growth and Spectroscopy of Altermagnetic MnTe, Marco Dittmar, H. Haberkamm, P. Kagerer, M. Ünzelmann, F. Reinert, University of Würzburg, Germany

As a new type of fundamental magnetic order next to ferromagnetism and antiferromagnetism, altermagnetism has recently attracted great attention. It is characterized by antiferromagnetic spin alignment combined with rotational lattice symmetry, which is reflected in a spin-split band structure with spin polarized electronic states. One of the "workhorse" materials potentially exhibiting this type of magnetic order is MnTe in its hexagonal NiAs-type crystal structure. Here, we investigate MnTe thin films grown on different substrates by molecular Thursday Evening, November 7, 2024

beam epitaxy. Using structural characterization methods, we discuss the influence of the growth parameters on the observed films. The electronic structure is assessed by soft X-ray angle-resolved photoemission spectroscopy and shows good agreement with band structure calculations. [1] L. Šmejkal et al., Phys. Rev. X 12, 031042 (2022)

### Friday Morning, November 8, 2024

#### Actinides and Rare Earths Room 123 - Session AC+MI-FrM

#### Actinide and Rare Earth Chemistry and Physics

Moderators: Edgar Buck, PNNL, Krzysztof Gofryk, Idaho National Laboratory, Gertrud Zwicknagl, Technical University Brauschweig

#### 8:15am AC+MI-FrM-1 Structure, Stability, and Chemistry of Actinide Nanoparticles, Ping Yang, G. Wang, E. Batista, Los Alamos National Laboratory INVITED

Nanoscale materials bearing heavy elements have a wide range of applications from the nuclear fuel cycle to environment and health. Nanocrystals (NCs) with size and shape dependent properties are a thriving research field and remarkable progress has been made in the controlled synthesis and characterization of NCs composed of stable elements in the past three decades. In this context, interfacial chemistry of nano-sized materials is critical for controlling the morphology that drives their unique associated chemical and physical properties. The understanding of NCs containing f-elements is comparatively limited due to difficulties in handling them both experimentally and theoretically. In this talk, I will share some recent progress in understanding the interplay between surface energy, surfactant ligands, and the chemistry in determining the morphology of 5felement nanoparticles. Quantum simulations provide a molecular-level picture of the relevant driving forces and dynamic properties. To push for larger lengthscale, we recently developed the density functional theory tight-binding (DFTB) parameters for actinide systems, that enabled the microsecond quantum MD simulations of actinide nanoparticle systems.

[1]G Wang, ER Batista, P Yang. Phys Chem Chem Phys2018, 20, 17563

[2]G Wang, ER Batista, P Yang, J. Phys Chem C, 2019, 123, 30245

[3]RK Carlson, MJ Cawkwell, ER Batista, P Yang, J. Chem. Thoery Compt2020, 16, 3073

[4]NF Aguirre, J Jung, P Yang, Phys Chem Chem Phys2020, 22, 18614

[5]G Wang, ER Batista, P Yang, Appl Sci2020, 10, 4655

[6]D G Gonzalez, G Wang, ER Batista, P Yang, Inorg Chem2023, in press

8:45am AC+MI-FrM-3 The Use of Ligand Modified Electrodes as Electrocatalysts for Actinide Redox Chemistry, Christopher Dares, Florida International University; T. Grimes, Idaho National Laboratory; J. McLachlan, University of California at Berkeley; X. Hou, University of Utah; A. Ruiz Reyes, Florida International University INVITED The lanthanides are most stable in the trivalent oxidation state, and with few exceptions, are difficult to generate in higher or lower oxidation states. In contrast the early actinides are redox active and can be generated and studied in a variety of oxidation states ranging from +7 to +2. This variety can complicate separations processes since oxidation state and can have a profound influence on ligand binding and solvent extraction. Separations schemes can also exploit the differences in binding preferences in different oxidation states to make selective extraction more efficient. In an aqueous acidic environment, the Am(IV/III) couple is at 2.6 V vs. the standard hydrogen electrode (SHE). This is nearly at the limit of what is possible in an aqueous solution where the 1-electron oxidation of water to hydroxyl radical is only about 0.3 V more positive. The subsequent potentials to generate penta- and hexavalent americium are lower though the high Am(IV/III) couple renders Am effectively redox-inert. Ligand coordination can be used to reduce the Am(IV/III) couple and/or facilitate the protoncoupled electron transfer (required to make the americyl cation). These can be organic ligands including N-donors or inorganic ligands such as lacunary polyoxometalates. Ligands anchored to metal oxide electrodes serve as good electrocatalysts to generate Am(V) or Am(VI) and operate at potentials as low as 1.6 V vs. SCE (nearly 1 V below the Am(IV/III) couple). Ligands are attached to the surface using either organic functional groups like phosphonic acids, or, through a combination of attractive interactions including hydrogen-bonding. They form well-packed monolayers on mesoporous thin layers of conductive oxides. The development of these ligand modified electrodes (LMEs) will be introduced along with characterization of their ability to adjust actinide oxidation states.

9:15am AC+MI-FrM-5 Observation of Flat Bands in Rare-Earth Based Kagome Metals, *Madhab Neupane*, University of Central Florida INVITED Quantum materials with kagome lattice – comprised of corner-sharing triangles forming a hexagon in the crystal structure - have been studied as the potential playgrounds for exploring the interplay among parameters

such as geometry, topology, electronic correlations, magnetic, and charge density orders. Recent report on a family of kagome metals of the form ReTi3Bi4 (Re = rare-earth) has generated interest due to the combination of highly anisotropic magnetism and a rich electronic structure. We use angle-resolved photoemission spectroscopy measurements in combination with density functional theory calculations to investigate the electronic structure of newly discovered kagome metals ReTi3Bi4. Our results reveal multiple van Hove singularities (VHSs), some of which are in the vicinity of the Fermi level. We clearly observe multiple flat bands, which originate from the destructive interference of wave functions within the Ti kagome motif. These flat bands and VHSs originate from Ti d-orbitals and are very responsive to the polarization of the incident beam. These results demonstrate that of Ti based kagome materials system is an excellent material platform for studying kagome induced flat band physics and its connection with magnetism.

#### 9:45am AC+MI-FrM-7 Kinetics and Mechanism of Plutonium Oxycarbide Formation, *Paul Roussel*, AWE plc, UK

Plutonium is both electropositive and highly reactive, such that an oxide film of varying thickness is always present on metal samples. It is of interest from a safety point of view (reduced handling/processing) to investigate methods that either prevent or slow down the rate of corrosion reaction of the metal. Plutonium oxycarbide, PuC<sub>1-x</sub>O<sub>x</sub>, surface films on plutonium metal have shown the ability to slow the rate of oxidation [1]. Favart et al. have reported the rate of plutonium oxycarbide formation at 350 °C [2] as measured using X-ray Diffraction. In the theoretical study reported by Qiu et al. the authors proposed four different mechanisms for the formation of plutonium oxycarbide [3]. Two of the proposed mechanisms involved the reaction of a gas with plutonium sesquioxide,  $Pu_2O_3$ , and the other two involved a solid state reaction of this oxide to form plutonium oxycarbide. Using a combination X-ray Photoelectron Spectroscopy, Secondary Ion Mass Spectrometry and X-ray Diffraction the kinetics and mechanism of plutonium oxycarbide formation have been investigated and will be presented.

[1] Retardation of plutonium oxidation by a PuO surface film, D. T. Larson, D. L. Cash, J. Vac. Sci. Technol. 9, 800 (1972).

[2] Characterization of PuO/PuCO phase and its influence on the oxidation kinetics of d-plutonium, N. Favart, B. Ravat, L. Jolly, B. Oudot, L. Berlu, F. Delaunay, I. Popa, S. Chevalier, Oxid. Met., 96, 271 (2021)

[3] Thermodynamical stability of plutonium monoxide with carbon substitution, R. Qiu, X. Wang, Y. Zhang, B. Ao, K. Liu, J. Phys. Chem. C 122, 22821 (2018).

10:00am AC+MI-FrM-8 Layered f-Metal Zintl Phases - EuZn<sub>2</sub>P<sub>2</sub> and UCu<sub>2</sub>P<sub>2</sub>, LADISLAV HAVELA, Charles University, Czech Republic; V. Buturlim, Idaho National Laboratory; O. Koloskova, Charles University, Prague, Czechia; D. Legut, J. Prchal, Charles University, Czech Republic; J. Kolorenc, J. Kastil, M. Misek, Institute of Physics CAS, Prague, Czechia

Zintl phases consisting of an electropositive element, cation, and covalently bonded polyanion, offer a large variability of electronic structure, bridging the gap between semiconducting and metallic behavior and offering interesting functionalities. In case of magnetic cation, properties can be further tuned by magnetic fields. Here we compare compounds based on lanthanide (Eu) and actinide (U) cations. We selected layered compounds, crystallizing in the trigonal structure CaAl<sub>2</sub>Si<sub>2</sub>, which exhibit pronounced magnetic anisotropy.  $EuZn_2P_2$  is a narrow band-gap semiconductor. Antiferromagnetic ordering of  $Eu^{2+}$  moments sets in at  $T_N$  = 23 K. Rapid increase of  $T_N$  with applied pressure, which reaches 43 K at p = 9.5 GPa, can be associated with reduction of the band gap, indicated by transport properties as well as by ab-initio calculations. Ferromagnetic alignment of Eu moments, achieved in fields of several Tesla, can reduce electrical resistivity by several orders of magnitude, which is classified as Colossal Magnetoresistance Effect. At p = 18 GPa (still within the same structure type), EuZn<sub>2</sub>P<sub>2</sub> becomes semi-metallic. The compression by hydrostatic pressure is anisotropic, with soft c-axis direction. UCu<sub>2</sub>P<sub>2</sub> with a smaller unit-cell volume is semi-metallic (and probably half-metallic) at ambient conditions. Also here the magnetic order (ferromagnetic) is supported by applied pressure, reaching 290 K at 6 GPa. The situation of 5f states is dramatically different comparing with the 4f states in the Eu counterpart. The indications given by large spontaneous magnetostriction, softer a-axis direction (nearest U-U links), or extremely strong uniaxial magnetocrystalline anisotropy point to an involvement of the 5f states in bonding, i.e. delocalization, although they do not contribute to the Fermi level, located in a pseudo-gap. Tuning by composition changes is not

### Friday Morning, November 8, 2024

straightforward for single crystals grown by Chemical Vapor Transport method, nevertheless certain routes have been attempted with a positive outcome and properties of doped UCu<sub>2</sub>P<sub>2</sub> will be discussed.

#### 10:30am AC+MI-FrM-10 Experimental Electronic Structure Measurements of Actinide-Containing Samples Using Scanning Tunneling Spectroscopy, *Benjamin Heiner*, M. Beaux, Los Alamos National Laboratory

The many difficulties performing experiments on plutonium-containing samples makes the prospect of studying them using computational methods enticing. The lag in collection of experimental data using modern techniques, especially related to electronic structure, has made validating computational methods challenging. With the establishment of a scanning tunneling microscope at Los Alamos National Laboratory with the capacity to study plutonium and other radioactive samples, the ability to probe electronic structure seamlessly across the Fermi energy is now possible. In a first of its kind experiment, scanning tunneling spectroscopy data on plutonium-containing samples, especially gallium-stabilized  $\delta$ -phase plutonium, has been collected. The spectra reveal a surface with semimetal characteristics instead of a computationally predicted semiconductor band gap.

LA-UR-24-24274

# 10:45am AC+MI-FrM-11 Unconventional Superconductivity in UBe<sub>13</sub> - Investigation via Variation of Impurity Level - and Comparison to the Conventional Superconductor LuBe<sub>13</sub>, *Greg stewart*, *J. Kim*, University of Florida

We have prepared and characterized down to T=0.40 K three arc-melted samples each of MBe13, M = Lu, U, using threedifferent purities (99.999%, 99.96%, and 99.8%) of Be but with the same high purity M (Lu or U) for all three.The measurements down to 0.40 K allow the detection of the maximum in the specific heat in all three LuBe13samples. The resulting superconducting properties strongly depend on impurity level in UBe13 (40% decrease in  $\Delta C/T_c$ , 15% decrease in  $T_c$ mid) while the three LuBe<sub>13</sub> samples exhibit significantly smaller changes (10% and 5% respectively) with purity. The comparison of properties at the first two levels of purity (99.999% vs 99.96%) iseven more disparate: 12% decrease in T<sub>c</sub>mid in UBe<sub>13</sub> vs no change in LuBe13. These results are consistent withprevious results that argue for unconventional superconductivity in UBe13, and are consistent with assignment of LuBe13 as a conventional, BCS superconductor. As will be discussed in more detail, this example of comparing superconducting properties vs controlled gradations in impurity levels with two compositionally and structurally "matched" superconducting compounds (one conventional and one of to-bedetermined coupling behavior) offers a new method - versus the already existing ones - for determining unconventional superconducting behavior.

#### 11:00am AC+MI-FrM-12 Strong Magnetoelastic Interactions in HoSb Probed by High-Resolution Dilatometry and X-Ray Diffraction, Volodymyr Buturlim, Glenn T. Seaborg Institute, Idaho National Laboratory; N. Poudel, Idaho National Laboratory; D. Kaczorowski, Polish Academy of Sciences, Poland; M. Jaime, Physikalisch Technische Bundesanstalt, Germany; Z. Islam, Argonne National Laboratory; K. Gofryk, Center for Quantum Actinide Science and Technology, Idaho National Laboratory

Rare-earth (RE) monopnictides, which crystallize in a cubic structure similar to NaCl have drawn considerable interest due to their diverse transport, magnetic, and structural properties. The non-magnetic compounds are known for the transition from topological to trivial electronic states (e.g. LaPn where Pn = Bi and As [1]). Magnetism of the compounds with longrange order brings complexity to their topological properties. However, the topological nature of these materials undergoes intense debates and investigation. HoSb is a topologically trivial semimetal, which orders antiferromagnetically below  $T_N$  = 5.7 K [2]. Application of magnetic field leads to the change of its magnetic structure from MnO-type antiferromagnetic (AFM) arrangement to HoP-type arrangement, then to ferromagnetic (FM) arrangement. There are also reports which, suggest a transition to tetragonal structure taking place at  $T_N$  [3]. The variety of the low-temperature phenomena makes HoSb a good platform to investigate the role of magnetic ordering and the strength of spin-phonon coupling on the crystal structure of this system. We will present the results of lowtemperature high-resolution dilatometry as well as X-ray diffraction studies performed at static and pulsed magnetic fields. Heat capacity studies and the presence of latent heat agree with the structural distortion that occurs at  $T_N$ . The lowering of the symmetry is further supported by detailed lowtemperature X-ray diffraction measurements under magnetic fields. Strong spin-lattice coupling in HoSb results in giant magnetostriction of the order of 1500 ppm. Furthermore, our detailed dilatometry studies allow us to

construct a magnetic phase diagram of HoSb. We will discuss the implications of these results in the context of the strong magnetoelastic properties in HoSb and other rare-earth monopnictides.

[1] H. Y. Yang et al., Phys. Rev. B 98, 045136 (2018).

[2] M. M. Hosen et al., Sci. Reports 2020 101 10, 1 (2020).

[3] F. Lévy, Phys. Kondons. Mater. 10, 85 (1969).

KG acknowledges the support from the Division of Materials Science and Engineering, Office of Basic Energy Sciences, Office of Science of the U. S. Department of Energy (U.S. DOE). VB acknowledges the support from the Idaho National Laboratory's Laboratory Directed Research and Development (LDRD) program under DOE Idaho Operations Office Contract DE-AC07-05ID14517.

#### 11:15am AC+MI-FrM-13 Electronic Structure in a Rare-Earth-Based Intermetallic System TbNi<sub>3</sub>Ga<sub>9</sub>, *Sabin Regmi*, V. Buturlim, Idaho National Laboratory; B. Rai, Savannah River National Laboratory; T. Durakiewicz, K. Gofryk, Idaho National Laboratory

Rare-earth-based intermetallics provide flexibility to study the electronic, magnetic, superconducting, and topological properties by tuning the crystal structure, composition, and spin-orbit coupling. Recently, RNi<sub>3</sub>(Ga/Al)<sub>9</sub> intermetallic materials have been studied for their richness in broad range of exotic crystal, magnetic, heavy fermion, and quantum criticality behaviors. However, momentum-resolved electronic structure studies are lacking. Here, we present results of the angle-resolved photoemission spectroscopy measurements to reveal the underlying electronic structure and topology in TbNi<sub>3</sub>Ga<sub>9</sub>, both above and below the Néel temperature. This study will open up exciting avenues towards exploration of electronic properties in the chiral family of RNi<sub>3</sub>(Ga/Al)<sub>9</sub> materials with wide range of intriguing properties.

#### 11:30am AC+MI-FrM-14 Catalytic Activities of Defected Actinide Dioxide Ano<sub>2</sub> Surface: A First Principles Study, *Shukai Yao, G. Wang, E. Batista, P. Yang,* Los Alamos National Laboratory

Actinide dioxides AnO<sub>2</sub> play an important role as nuclear fuels in commercial nuclear reactors. Understanding the surface chemistry of AnO<sub>2</sub> is crucial in various aspects such as safe operations, recycling, and storage of nuclear fuels. Actinide materials have shown to be highly efficient catalyst for the activation of H<sub>2</sub>, CO, NH<sub>3</sub>, etc., mainly due to valent 5*f* electrons of actinides characterized by strong electron correlations and various oxides states. However, experimental studies of actinide systems are limited by their high safety requirement associated with radioactivity. In this computational study, we employed first principles electronic structure calculations based on density functional theory (DFT) to reveal the catalytic behavior of AnO<sub>2</sub> surface with O vacancies. We will show that O vacancies significantly change the electronic structure of AnO<sub>2</sub> surfaces, and act as the active sites of small molecules adsorption. As a result, defected AnO<sub>2</sub> surface.

## 11:45am AC+MI-FrM-15 Thin Film Synthesis of Rare Earth and Actinide Nitrides Using Molecular Beam Epitaxy, *Keivn Vallejo*, B. May, Z. Cresswell, V. Buturlim, S. Regmi, K. Gofryk, Idaho National Laboratory

Lanthanide- and actinide-based nitride compounds are an understudied group of materials compared to their oxide counterparts, which provide new avenues for nuclear reactor designs. Their 4f and 5f electron shell gives rise to a variety of interesting physics such as magnetism and unconventional superconductivity. Samarium nitride (SmN) has been recently identified as a material where ferromagnetic order and potential ptype superconductivity coexist. Our team will present results on the growth conditions in a molecular beam epitaxy chamber of pure and doped SmN using molecular beam epitaxy, and its electronic transport properties as a function of temperature and magnetic field. CeN and UN thin films are also explored. The presence of SmN(111) peaks on (001) substrates indicates an orientation-preference for some material systems. The electrical resistivity and magnetic susceptibility studies have shown a range of magnetic behaviors, including paramagnetic and ferromagnetic. With a potential superconductive transition around ~10 K, SmN and its doping effects on crystal structure and electronic properties are characterized.

#### **Author Index**

Bold page numbers indicate presenter

Elfimov, Ilya: AC+MI-ThM-3, 7

- E -

— A —

Abbas, Ali: MI+2D+AC+TF-WeA-4, 5; MI+2D+AC+TF-WeM-7, 3; MI+2D+AC+TF-WeM-8, 3; MI-ThP-1, 11 Argyropoulos, Christos: MI+2D+AC+TF-WeA-10, 6 Asselberghs, Inge: 2D+EM+MI+QS-WeM-4, 1 Azcatl, Angelica: 2D+EM+MI+QS-WeM-13, 2 – B – Babayew, Rami: AC+MI-ThM-13, 8 Baker, Alexander: AC+MI-ThA-6, 9; AC+MI-ThA-7.9 Balicas, Luis: 2D+EM+MI+QS-WeM-15, 2 Bansil, Arun: MI+2D+AC+TF-WeA-3, 5 Barreto, Lucas: MI+2D+AC+TF-WeM-14, 4 Batista, Enrique: AC+MI-FrM-1, 12; AC+MI-FrM-14, 13 Bauer, Eric D.: AC+MI-ThM-3, 7 Beaux, Miles: AC+MI-FrM-10, 13; AC+MI-ThA-8, 10 Bentmann, Hendrik: MI+2D+AC+TF-WeM-1, 2 Bhandari, Ghadendra: MI+2D+AC+TF-WeM-4,3 Bhattacharjee, Nirjhar: MI+2D+AC+TF-WeA-3.5 Binek, Christian: MI+2D+AC+TF-WeA-10, 6 Borgschulte, Andreas: MI+2D+AC+TF-WeA-11, 6 Brackbill, Joseph: AC+MI-ThA-6, 9 Briley, Chad: MI+2D+AC+TF-WeA-10, 6 Buck, Edgar: AC+MI-ThA-5, 9 Buturlim, Voldymyr: AC+MI-FrM-15, 13 Buturlim, Volodymyr: AC+MI-FrM-12, 13; AC+MI-FrM-13, 13; AC+MI-FrM-8, 12 -c-Canto, Barbara: 2D+EM+MI+QS-WeM-4, 1 Chen, Charlene: 2D+EM+MI+QS-WeM-13, 2 Cheng, Ching-Jung: 2D+EM+MI+QS-WeM-13, 2 Chi, Hang: MI+2D+AC+TF-WeA-1, 5 Christovam, Denise S.: AC+MI-ThM-3, 7; AC+MI-ThM-7, 7 Chung, Brandon: AC+MI-ThA-6, 9; AC+MI-ThA-7, **9** Cicchetti, Nic: AC+MI-ThA-6, 9 Cicchetti, Nick: AC+MI-ThA-7, 9 Clark, Mark: 2D+EM+MI+QS-WeM-13, 2 Coles, Rebecca: AC+MI-ThA-6, 9 Cresswell, Zachery: AC+MI-FrM-15, 13 Croce, Mark: AC+MI-ThA-3, 9 Cui, Alex: 2D+EM+MI+QS-WeM-7, 1 Cunha, Carlos: 2D+EM+MI+QS-WeM-4, 1 – D – Dares, Christopher: AC+MI-FrM-3, 12 Darwin, Emily: MI+2D+AC+TF-WeA-11, 6 De Gendt, Stefan: 2D+EM+MI+QS-WeM-4, 1 de Marneffe, Jean-Francois: 2D+EM+MI+QS-WeM-4.1 Deshpande, Vikram: 2D+EM+MI+QS-WeM-5, 1 Dewasurendra, Vikum: MI+2D+AC+TF-WeM-4.3 Ditter, Alexander: AC+MI-ThA-6, 9; AC+MI-ThA-7, 9 Dittmar, Marco: MI-ThP-4, 11 Donald, Scott: AC+MI-ThA-6, 9; AC+MI-ThA-7,9 Donath, Markus: MI+2D+AC+TF-WeM-13, 4 Dryzhakov, Bogdan: MI+2D+AC+TF-WeA-9, 6 Dubs, Carsten: MI+2D+AC+TF-WeA-3, 5 Duffin, Andrew: AC+MI-ThA-6, 9 Dunn, Stuart: AC+MI-ThA-1, 9 Durakiewicz, Tomasz: AC+MI-FrM-13, 13

Elgad, Noam: AC+MI-ThM-13, 8 Erickson, Tyler: MI+2D+AC+TF-WeM-7, 3; MI-ThP-1. 11 — F — Feder, Rene: MI+2D+AC+TF-WeA-10, 6 Figgemeier, Tim: MI+2D+AC+TF-WeM-1, 2 Flavell, Wendy: AC+MI-ThA-1, 9 Friedman, Adam L.: 2D+EM+MI+QS-WeM-3, 1 Fujimori, Shin-ichi: AC+MI-ThM-1, 7 - G -Gai, Zheng: MI+2D+AC+TF-WeM-3, 2 Gayles, Jacob: MI+2D+AC+TF-WeM-15, 4; MI-ThP-3, 11 Geldiyev, Begmuhammet: MI+2D+AC+TF-WeM-1, 2 Gloskovskii, Andrei: AC+MI-ThM-3, 7; AC+MI-ThM-7, 7 Gofryk, Krzysztof: AC+MI-FrM-12, 13; AC+MI-FrM-13, 13; AC+MI-FrM-15, 13; AC+MI-ThM-15,8 Green, Robert: MI+2D+AC+TF-WeM-14, 4 Gretarsson, Hlynur: AC+MI-ThM-7, 7 Gretarsson, Hylnur: AC+MI-ThM-3, 7 Grimes, Travis: AC+MI-FrM-3, 12 Griveau, J-C: AC+MI-ThM-15, 8 Grutter, Alexander: MI+2D+AC+TF-WeA-3, 5 Grutter, Karen E.: 2D+EM+MI+QS-WeM-3, 1 Gunther, Olivia: AC+MI-ThA-6, 9; AC+MI-ThA-7, 9 — H — Haberkamm, Hannes: MI-ThP-4, 11 Halevy, Itzhak: AC+MI-ThM-13, 8 Hall, Hannah: MI+2D+AC+TF-WeM-7, 3; MI-ThP-1.11 Hammer, Lutz: MI+2D+AC+TF-WeM-13, 4 Hanbicki, Aubrey T.: 2D+EM+MI+QS-WeM-3, 1 Hariki, Atsushi: AC+MI-ThM-7, 7 Harrison, Ian: MI+2D+AC+TF-WeM-3, 2 Harrison, Robert: AC+MI-ThA-1, 9 HAVELA, LADISLAV: AC+MI-FrM-8, 12 Haverkort, Maurits W.: AC+MI-ThM-3, 7 He, Gaohang: 2D+EM+MI+QS-WeM-4, 1 Heiman, Don: MI+2D+AC+TF-WeA-3, 5 Heiner, Benjamin: AC+MI-FrM-10, 13 Higginson, Matthew: AC+MI-ThA-1, 9 Holcomb, Mikel: MI+2D+AC+TF-WeM-4, 3 Hou, Xiangyang: AC+MI-FrM-3, 12 Hu, Bin: MI+2D+AC+TF-WeA-9, 6 Hug, Hans Josef: MI+2D+AC+TF-WeA-11, 6 -1-Ingram, David: MI-ThP-1, 11 Ingram, David C.: MI+2D+AC+TF-WeA-4, 5 Islam, Zahir: AC+MI-FrM-12, 13 \_\_ J \_\_ J. Lockhart de la Rosa, Cesar: 2D+EM+MI+QS-WeM-4, 1 Jaime, Marcelo: AC+MI-FrM-12, 13 Jangid, Rahul: 2D+EM+MI+QS-WeM-7, 1 Jin, Rongying: MI+2D+AC+TF-WeM-3, 2 Johnson, Matthew: MI+2D+AC+TF-WeM-4, 3 —к— Kaczorowski, Dariusz: AC+MI-FrM-12, 13 Kagerer, Philipp: MI-ThP-4, 11 Kanjolia, Ravi: 2D+EM+MI+QS-WeM-13, 2 Karbasizadeh, Siavash: MI+2D+AC+TF-WeM-3, 2 Kastil, Jiri: AC+MI-FrM-8, 12 Katarivas-Levy, Galit: AC+MI-ThM-13, 8 Kaya, Savas: MI-ThP-1, 11 Kaye, Philip: AC+MI-ThA-1, 9

Keimer, Bernhard: AC+MI-ThM-3, 7; AC+MI-ThM-7.7 Kilic, Ufuk: MI+2D+AC+TF-WeA-10, 6 Kim, Jungsoo: AC+MI-FrM-11, 13 Kim, Philip: 2D+EM+MI+QS-WeM-7, 1 Kißlinger, Tilman: MI+2D+AC+TF-WeM-13, 4 Knafo, William: AC+MI-ThM-5, 7 Kolorenc, Jindrich: AC+MI-FrM-8, 12 Koloskova, Oleksandra: AC+MI-FrM-8, 12 Kong, Dejia: MI+2D+AC+TF-WeM-3, 2 Koroluk, Skylar: MI+2D+AC+TF-WeM-14, 4 Krüger, Peter: MI+2D+AC+TF-WeM-13, 4 Kumar, Uma Mahendra: MI-ThP-1, 11 Kunes, Jan: AC+MI-ThM-7, 7 -L-Last, Mark: AC+MI-ThM-13, 8 Lauter, Valeria: MI+2D+AC+TF-WeA-3, 5; MI+2D+AC+TF-WeA-9, 6 Le, Son T.: 2D+EM+MI+QS-WeM-3, 1 Lefler, Benjamin: MI+2D+AC+TF-WeM-14, 4 Legut, Dominik: AC+MI-FrM-8, 12 Li, Tian: AC+MI-ThA-7, 9 Lidsky, David: MI+2D+AC+TF-WeA-3, 5 Lim, Rachel: AC+MI-ThA-6, 9; AC+MI-ThA-7, 9 Lindner, Morris: MI+2D+AC+TF-WeA-3, 5 Longo, Filippo: MI+2D+AC+TF-WeA-11, 6 Lorincik, Jan: AC+MI-ThM-13, 8 Lu, Tzu-Ming: MI+2D+AC+TF-WeA-3, 5 Luo, Bin: MI+2D+AC+TF-WeA-3, 5 -M-Marino, Andrea: AC+MI-ThM-3, 7; AC+MI-ThM-7, 7 Matzelle, Matthew: MI+2D+AC+TF-WeA-3, 5 May, Brelon: AC+MI-FrM-15, 13 May, Steven: MI+2D+AC+TF-WeM-14, 4 Mazzoli, Claudio: 2D+EM+MI+QS-WeM-7, 1 McEwen, K. A.: AC+MI-ThM-15, 8 McLachlan, Jeffrey: AC+MI-FrM-3, 12 Mehta, Uday: AC+MI-ThA-7, 9 Merckling, Clement: 2D+EM+MI+QS-WeM-4, Miller, Micah: AC+MI-ThA-6, 9 Miller, Michael: 2D+EM+MI+QS-WeM-13, 2 Misek, Martin: AC+MI-FrM-8, 12 Mock, Alyssa: MI+2D+AC+TF-WeA-10, 6 Moinpour, Mansour: 2D+EM+MI+QS-WeM-13, 2 Monson, Todd C.: MI+2D+AC+TF-WeA-3, 5 Mu, Sai: MI+2D+AC+TF-WeM-3, 2 Narasimha, Ganesh: MI+2D+AC+TF-WeM-3, Nellis, W. J.: AC+MI-ThM-15, 8 Neupane, Madhab: AC+MI-FrM-5, 12 Ngo, Thong: 2D+EM+MI+QS-WeM-13, 2 -0-Orion, Itzhak: AC+MI-ThM-13, 8 -P-Pantano, Gina: MI+2D+AC+TF-WeM-15, 4 Pearce, Charles J.: MI+2D+AC+TF-WeA-3, 5 Peremadathil Pradeep, Reshma: MI+2D+AC+TF-WeA-11, 6 Poccia, Nicola: 2D+EM+MI+QS-WeM-7, 1 Poudel, Narayan: AC+MI-FrM-12, 13 Prchal, Jiri: AC+MI-FrM-8, 12 Puggioni, Danilo: MI+2D+AC+TF-WeM-14, 4 — R – Rai, Binod K.: AC+MI-FrM-13, 13 Rajasabai, Senthur Pandi: MI-ThP-1, 11 Regmi, Paras: MI+2D+AC+TF-WeM-3, 2 Regmi, Sabin: AC+MI-FrM-13, 13; AC+MI-FrM-15.13 Reimann, Timmy: MI+2D+AC+TF-WeA-3, 5 Bold page indicates presenter

Author Index

#### **Author Index**

Reinert, Friedrich: MI+2D+AC+TF-WeM-1, 2; MI-ThP-4, 11 Rogge, Paul: MI+2D+AC+TF-WeM-14, 4 Rondinelli, James: MI+2D+AC+TF-WeM-14, 4 Rosa, Priscila F. S.: AC+MI-ThM-3, 7 Rosas, Debra: AC+MI-ThA-7, 9 Roussel, Paul: AC+MI-FrM-7, 12; AC+MI-ThA-1, 9 Ruiz Reyes, Alberto: AC+MI-FrM-3, 12 Russell, Daniel: MI+2D+AC+TF-WeM-8, 3; MI-ThP-1, 11 — s — Sankar Kar, Gouri: 2D+EM+MI+QS-WeM-4, 1 Schmidt, Heidemarie: MI+2D+AC+TF-WeA-10,6 Schneider, M. Alexander: MI+2D+AC+TF-WeM-13.4 Schöttke, Fabian: MI+2D+AC+TF-WeM-13, 4 Schubert, Eva: MI+2D+AC+TF-WeA-10, 6 Schubert, Mathias: MI+2D+AC+TF-WeA-10, 6 Schwartz, Jeffrey J.: 2D+EM+MI+QS-WeM-3, 1 Sekora, Derek: MI+2D+AC+TF-WeA-10, 6 Servando-Williams, Donya: AC+MI-ThA-7, 9 Severing, Andrea: AC+MI-ThM-3, 7; AC+MI-ThM-7, 7 Sharma, Peter: MI+2D+AC+TF-WeA-3, 5 Shrestha, Ashok: MI+2D+AC+TF-WeA-4, 5; MI+2D+AC+TF-WeM-7, 3; MI+2D+AC+TF-WeM-8, 3; MI-ThP-1, 11

Shuh, David: AC+MI-ThA-6, **9**; AC+MI-ThA-7, 9

Sinova, Jairo: MI+2D+AC+TF-WeM-15, 4 Sinsheimer, John: 2D+EM+MI+QS-WeM-7, 1 Slaets, Robbe: 2D+EM+MI+QS-WeM-4, 1 Šmejkal, Libor: MI+2D+AC+TF-WeM-15, 4; MI+2D+AC+TF-WeM-5, 3 Smith, Arthur: MI+2D+AC+TF-WeM-7, 3; MI-ThP-1, 11 Smith, Arthur R.: MI+2D+AC+TF-WeA-4, 5; MI+2D+AC+TF-WeM-8, 3 Smith, J. L.: AC+MI-ThM-15, 8 Spencer, Ben: AC+MI-ThA-1, 9 Srikanth, Hari: MI+2D+AC+TF-WeA-5, 6 stewart, Greg: AC+MI-FrM-11, 13 Sun, Nian Xiang: MI+2D+AC+TF-WeA-3, 5 Sundermann, Martin: AC+MI-ThM-3, 7; AC+MI-ThM-7,7 Sutter, Eli: 2D+EM+MI+QS-WeM-1, 1 Sutter, Peter: 2D+EM+MI+QS-WeM-1, 1 —т— Tao, Chenggang: MI+2D+AC+TF-WeM-3, 2 Tavazohi, Pedram: MI+2D+AC+TF-WeM-4, 3 Thareja, Eklavya: MI+2D+AC+TF-WeM-15, 4; MI-ThP-3.11 Timmermans, Marina: 2D+EM+MI+QS-WeM-4.1 Tjeng, Liu Hao: AC+MI-ThM-3, 7; AC+MI-ThM-7.7 Tkacik, Samuel: MI-ThP-3, 11 Tobin, JG: AC+MI-ThA-9, 10 Ullah, Ahsan: MI+2D+AC+TF-WeA-10, 6

Ünzelmann, Maximilian: MI+2D+AC+TF-WeM-1, 2; MI-ThP-4, 11 Upadhyay, Sneha: MI+2D+AC+TF-WeM-7, 3; MI-ThP-1, 11 \_v\_ Valdez, Nichole R.: MI+2D+AC+TF-WeA-3, 5 Vallejo, Keivn: AC+MI-FrM-15, 13 Vasudevan, Rama: MI+2D+AC+TF-WeM-3, 2 Vu, Nguyen: 2D+EM+MI+QS-WeM-13, 2 \_w\_ Wang, Gaoxue: AC+MI-FrM-1, 12; AC+MI-FrM-14, 13 Wang, Jiayi: MI+2D+AC+TF-WeM-14, 4 Wang, Zhenxing: 2D+EM+MI+QS-WeM-4, 1 Ward, Jesse: AC+MI-ThA-6, 9 Wasik, Patryk: 2D+EM+MI+QS-WeM-7, 1 Weiss, Aryeh M.: AC+MI-ThM-13, 8 Willcole, Alexandria: MI+2D+AC+TF-WeA-3, 5 Wood, Aaron: AC+MI-ThA-1, 9 Wyndaele, Pieter-Jan: 2D+EM+MI+QS-WeM-4.1 — Y — Yang, Fengyuan: MI+2D+AC+TF-WeM-8, 3; MI-ThP-1, 11 Yang, Ping: AC+MI-FrM-1, 12; AC+MI-FrM-14, 13 Yao, Shukai: AC+MI-FrM-14, 13 Yehuda-Zada, Yaacov: AC+MI-ThM-13, 8 -z-Zhao, Shu Yang Frank: 2D+EM+MI+QS-WeM-7, 1

Zwicknagl, Gertrud: AC+MI-ThM-14, 8