

Supplemental Document:

Sample	Thickness (nm)	Stress (MPa) (Post Deposition)	Stress (MPa) (After 7 Months)	Stress Change (MPa)
1	176	-343	-249	+94
2	173	-354	-275	+79
3	172	-356	-289	+67

