

Fig. 1 Cubic-like NaNbO_3 fabricated using 30 mM Nb_2O_5 , 3 M NaOH, and annealed at 150 °C for 48 h.




Fig. 2 Cross-stacking thin plate-like NaNbO_3 fabricated using 60 mM Nb_2O_5 , 12 M NaOH, and annealed at 160 °C for 4 h.




Fig. 3 Cross-stacking thick plate-like NaNbO_3 fabricated using 60 mM Nb_2O_5 , 12 M NaOH, and annealed at 160 °C for 12 h.