



**Figure 1** – a) Schematic structure of test structure to study impacts of plasma bulbs and Si dopant source during growth interrupts. b) TOF-SIMS depth profile showing Si only accumulates at the sample surface during growth interrupts while the Si cell was hot enough to provide a Si flux while no Si accumulated regardless of exposure time to just the quartz plasma bulb with a 250W O plasma.