Photo-driven dipole reordering: key to carrier separation in metalorganic halide perovskites

H.-C. Hsu¹, B.-C. Huang², S.-C. Chin¹, C.-R. Hsing², D.-L. Nguyen^{2, 6, 7}, M. Schnedler³, R. Sankar^{4, 8}, R. E. Dunin-Borkowski³, C.-M. Wei^{2, 6}, C.-W. Chen^{5, 9, 10}, <u>Ph. Ebert³</u>, and Ya-Ping Chiu^{1, 9}

¹ Dept. of Physics, National Taiwan University, Taipei 10617, Taiwan
² Institute of Atomic and Molecular Sciences, Academia Sinica, Taipei 10617, Taiwan
³ Peter Grünberg Institut, Forschungszentrum Jülich GmbH, 52425 Jülich, Germany
⁴ Institute of Physics, Academia Sinica, Taipei 11529, Taiwan

⁵ Dept. of Mat. Sci. and Eng., National Taiwan University, Taipei 10617, Taiwan

⁶ Molecular Sci. and Technol. Program, TIGP, Academia Sinica, Taipei 10617, Taiwan

⁷ Dept. of Physics, National Central University, Taoyuan City 32001, Taiwan

⁸ Center for Condensed Matter Sci., National Taiwan University, Taipei 10617, Taiwan

⁹ Center of Atomic Initiative for New Materials, National Taiwan University, Taipei 10617,

Taiwan

¹⁰ Taiwan Consortium of Emergent Crystalline Materials (TCECM), Ministry of Science and Technology, Taipei 10617, Taiwan

Photo-driven dipole reordering of the intercalated organic molecules in halide perovskites has been suggested to be a critical degree of freedom, potentially affecting physical properties, device performance, and stability of hybrid perovskite–based optoelectronic devices. However, thus far a direct atomically-resolved dipole mapping under device operation condition, i.e. illumination, is lacking. Here, we map simultaneously the molecule dipole orientation pattern and the electrostatic potential with atomic resolution using light-illuminated cross-sectional scanning tunneling microscopy and spectroscopy.

Our experimental observations demonstrate that a photo-driven dipole reordering, initiated by a photo-excited separation of electron-hole pairs in spatially displaced orbitals, leads to a fundamental reshaping of the potential landscape in halide perovskites, creating separate one-dimensional transport channels for holes and electrons. We anticipate that analogous light-induced polarization order transitions occur in bulk and are at the origin of the extraordinary efficiencies of organometal halide perovskite-based solar cells as well as could reconcile apparently contradictory materials' properties.




Figure 1 Illustration of lightinduced structure and potential changes at $CH_3NH_3PbBr_3$ surfaces. (A) 2×2 phase in dark and (B) illumination-induced 4×2 phase. Superimposed are the constant-current STM images (left side) and electrostatic potential energy landscapes (right).

⁺ Author for correspondence: p.ebert@fz-juelich.de